



250 Chester Street
 Painesville, Ohio 44077
 Phone: 866-GO-AVERY (866-462-8379)
 Fax: 888-358-4469
 email: psa.tape@averydennison.com
 URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 1115
 SUPPORT: LEATHER
 SUBSTRATE: FIBER BOARD
 CERT NO.: 230103 - 0950



FCA MS-CB-134

OEM Rev Date: Dec 16

Adhesive - Water Based or PSA Film - Interior Grade - One Coat System
 Type B - This adhesive is received pre applied to vinyl fabric or body cloth. The adhesive when heated becomes pressure sensitive, permitting a bond to a rigid substrate with the application of pressure.

TEST PARAMETERS:

SECTION:	TEST NAME	TEST CONDITIONS	Specification	Results	Status
3.2	Adhesive Peel Strength	Initial, 24 hrs @ RT	2.7 N / cm	3.3	Pass
3.2	Adhesive Peel Strength	LP-463CB-10-01 168 hrs @ 79°C	1.8 N / cm	17.9	Pass
3.2	Adhesive Peel Strength	ASTM D1733CB-10-01 168 hrs @ 38°C / 98% RH	2.2 N / cm	11.3	Pass
3.2	Adhesive Peel Strength	LP-463CB-10-01 Cycles, 3X 24 hrs @ 79°C 24 hrs @ 38°C / 95% RH 24 hrs @ -29°C	2.2 N / cm	18.2	Pass
3.3	Shear Adhesion	Initial, 24 hrs @ RT	55 kPa	426.3	Pass
3.3	Shear Adhesion	LP-463CB-10-01 168 hrs @ 79°C	48 kPa	560.3	Pass
3.3	Shear Adhesion	ASTM D1735 168 hrs @ 38°C / 98% RH	55 kPa	659.7	Pass
3.3	Shear Adhesion	LP-463CB-10-01 Cycles, 3X 24 hrs @ 79°C 24 hrs @ 38°C / 95% RH 24 hrs @ -29°C	55 kPa	442.4	Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.