



250 Chester Street  
Painesville, Ohio 44077  
Phone: 866-GO-AVERY (866-462-8379)  
Fax: 888-358-4469  
email: psa.tape@averydennison.com  
URL: tapes.averydennison.com

### TEST REPORT

PRODUCT: FT 1126  
SUPPORT: ALCANTERA  
SUBSTRATE: FIBER BOARD  
CERT NO.: 230103 - 0951



**FCA MS-CB-134**

OEM Rev Date: Dec 16

Adhesive - Water Based or PSA Film - Interior Grade - One Coat System  
Type B - This adhesive is received pre applied to vinyl fabric or body cloth. The adhesive when heated becomes pressure sensitive, permitting a bond to a rigid substrate with the application of pressure.

**TEST PARAMETERS:**

SECTION:	Test Name	Spec	Specification	Results	Status
SECTION: 3.2	Adhesive Peel Strength		2.7 N / cm	6.6	Pass
Initial, 24 hrs @ RT					
SECTION: 3.2	Adhesive Peel Strength	LP-463CB-10-01	1.8 N / cm	11.0	Pass
168 hrs @ 79°C					
SECTION: 3.2	Adhesive Peel Strength	ASTM D1733CB-10-01	2.2 N / cm	9.5	Pass
168 hrs @ 38°C / 98% RH					
SECTION: 3.2	Adhesive Peel Strength	LP-463CB-10-01	2.2 N / cm	8.4	Pass
Cycles, 3X					
24 hrs @ 79°C					
24 hrs @ 38°C / 95% RH					
24 hrs @ -29°C					
SECTION: 3.3	Shear Adhesion		55 kPa	211.1	Pass
Initial, 24 hrs @ RT					
SECTION: 3.3	Shear Adhesion	LP-463CB-10-01	48 kPa	291.2	Pass
168 hrs @ 79°C					
SECTION: 3.3	Shear Adhesion	ASTM D1735	55 kPa	161.1	Pass
168 hrs @ 38°C / 98% RH					
SECTION: 3.3	Shear Adhesion	LP-463CB-10-01	55 kPa	131.4	Pass
Cycles, 3X					
24 hrs @ 79°C					
24 hrs @ 38°C / 95% RH					
24 hrs @ -29°C					

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.