



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 1126
SUPPORT: LEATHER
SUBSTRATE: FIBER BOARD
CERT NO.: 230103 - 0951



FCA MS-CB-134

OEM Rev Date: Dec 16

Adhesive - Water Based or PSA Film - Interior Grade - One Coat System
Type B - This adhesive is received pre applied to vinyl fabric or body cloth. The adhesive when heated becomes pressure sensitive, permitting a bond to a rigid substrate with the application of pressure.

TEST PARAMETERS:

SECTION:	TEST TYPE	CONDITIONS	Specification	Results	Status
3.2	Adhesive Peel Strength	Initial, 24 hrs @ RT	2.7 N / cm	6.7	Pass
3.2	Adhesive Peel Strength	LP-463CB-10-01 168 hrs @ 79°C	1.8 N / cm	12.0	Pass
3.2	Adhesive Peel Strength	ASTM D1733CB-10-01 168 hrs @ 38°C / 98% RH	2.2 N / cm	13.5	Pass
3.2	Adhesive Peel Strength	LP-463CB-10-01 Cycles, 3X 24 hrs @ 79°C 24 hrs @ 38°C / 95% RH 24 hrs @ -29°C	2.2 N / cm	12.8	Pass
3.3	Shear Adhesion	Initial, 24 hrs @ RT	55 kPa	245.9	Pass
3.3	Shear Adhesion	LP-463CB-10-01 168 hrs @ 79°C	48 kPa	333.9	Pass
3.3	Shear Adhesion	ASTM D1735 168 hrs @ 38°C / 98% RH	55 kPa	245.9	Pass
3.3	Shear Adhesion	LP-463CB-10-01 Cycles, 3X 24 hrs @ 79°C 24 hrs @ 38°C / 95% RH 24 hrs @ -29°C	55 kPa	266.4	Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.