

250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

Fax: **888-358-4469**

email: psa.tape@averydennison.com

URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 1126

SUPPORT: TAN NONWOVEN

SUBSTRATE: ABS

CERT NO.: 230103 - 0951



OEM Rev Date: Dec 16

Adhesive - Water Based or PSA Film - Interior Grade - One Coat System Type B - This adhesive is received pre applied to vinyl fabric or body cloth. The adhesive when heated becomes pressure sensitive, permitting a bond to a rigid

ACCREDITED

TESTING LABORATORY

substrate with the application of pressure.

TEST PARAMETERS:

SECTION: 3.2 Adhesive Peel Strength Specification Results Status
Initial, 24 hrs @ RT 5.6 Pass

 SECTION: 3.2
 Adhesive Peel Strength
 LP-463CB-10-01
 Specification
 Results
 Status

 168 hrs @ 79°C
 1.8 N / cm
 3.9
 Pass

 SECTION: 3.2
 Adhesive Peel Strength
 ASTM D17:53CB-10-01
 Specification
 Results
 Status

 168 hrs @ 38°C / 98% RH
 2.2 N / cm
 7.0
 Pass

SECTION: 3.2 Adhesive Peel Strength LP-463CB-10-01 Specification Results Status

Cycles, 3X 2.2 N / cm 3.0 Pass

24 hrs @ 79°C

24 hrs @ 38°C / 95% RH

24 hrs @ -29°C

SECTION: 3.3 Shear Adhesion Specification Results Status
Initial, 24 hrs @ RT 139.4 Pass

SECTION: 3.3 Shear Adhesion LP-463CB-10-01 Specification Results Status

168 hrs @ 79°C 48 kPa 99.8 Pass

 SECTION: 3.3
 Shear Adhesion
 ASTM D1735
 Specification
 Results
 Status

 168 hrs @ 38°C / 98% RH
 55 kPa
 125.3
 Pass

SECTION: 3.3 Shear Adhesion LP-463CB-10-01 Specification Results Status

Cycles, 3X Shear Adhesion LP-463CB-10-01 Specification 96.4 Pass

Cycles, 3X 24 hrs @ 79°C

24 hrs @ 38°C / 95% RH

24 hrs @ -29°C

CERTIFIED BY: ISSUE DATE: 1-1-24

Dave Nichols Jr. Automotive Lab Technician

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.