

250 Chester Street Painesville, Ohio 44077

866-GO-AVERY (866-462-8379) Phone:

Fax: 888-358-4469

email: psa.tape@averydennison.com

URL: tapes.averydennison.com

## **TEST REPORT**

PRODUCT: FT 1126

SUPPORT: **TAN NONWOVEN** SUBSTRATE: FIBER BOARD 230103 - 0952 CERT NO.:



FCA MS-CB-134

OEM Rev Date: Dec 16

Adhesive - Water Based or PSA Film - Interior Grade - One Coat System Type B - This adhesive is received pre applied to vinyl fabric or body cloth. The adhesive when heated becomes pressure sensitive, permitting a bond to a rigid substrate with the application of pressure.

TEST	PARAMETERS:
------	-------------

1691 PAKAWETE					
SECTION: 3.2 Initial, 24 hrs @ RT	Adhesive Peel Strength		Specification 2.7 N / cm	<u>Results</u> 6.7	Status Pass
SECTION: <b>3.2</b> 168 hrs @ 79°C	Adhesive Peel Strength	LP-463CB-10-01	Specification 1.8 N / cm	Results 2.7	Status Pass
SECTION: <b>3.2</b> 168 hrs @ 38°C / 9	Adhesive Peel Strength 8% RH	ASTM D17533CB-10-01	Specification 2.2 N / cm	Results 5.6	Status Pass
24 hrs (	Adhesive Peel Strength  @ 79°C  @ 38°C / 95% RH  @ -29°C	LP-463CB-10-01	Specification 2.2 N / cm	Results 3.2	Status Pass
SECTION: 3.3 Initial, 24 hrs @ RT	Shear Adhesion		Specification 55 kPa	Results 160.0	Status Pass
SECTION: <b>3.3</b> 168 hrs @ 79°C	Shear Adhesion	LP-463CB-10-01	Specification 48 kPa	Results 82.5	Status Pass
SECTION: <b>3.3</b> 168 hrs @ 38°C / 9	<b>Shear Adhesion</b> 8% RH	ASTM D1735	Specification 55 kPa	Results 128.0	Status Pass
SECTION: 3.3 Cycles, 3X	Shear Adhesion  @ 79°C	LP-463CB-10-01	Specification 55 kPa	<u><b>Results</b></u> 76.9	Status Pass

**CERTIFIED BY:** 

ISSUE DATE:

Dave Nichols Jr, Automotive Lab Technician

24 hrs @ 38°C / 95% RH

24 hrs @ -29°C

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.