

888-358-4469

866-GO-AVERY (866-462-8379)

psa.tape@averydennison.com

tapes.averydennison.com

250 Chester Street

Phone:

Fax:

email:

URL:

Painesville, Ohio 44077

TEST REPORT

PRODUCT:	FT 1149X
SUPPORT:	GRAY VINYL
SUBSTRATE:	ABS
CERT NO .:	230103 - 0952



FCA MS-CB-134

OEM Rev Date: Dec 16

Adhesive - Water Based or PSA Film - Interior Grade - One Coat System Type B - This adhesive is received pre applied to vinyl fabric or body cloth. The adhesive when heated becomes pressure sensitive, permitting a bond to a rigid substrate with the application of pressure.

TEST PARAMETE SECTION: 3.2 Initial, 24 hrs @ RT	Adhesive Peel Strength		Specification 2.7 N / cm	Results 18.0	<u>Status</u> Pass
SECTION: 3.2 168 hrs @ 79°C	Adhesive Peel Strength	LP-463CB-10-01	Specification 1.8 N/cm	Results 7.0	<u>Status</u> Pass
SECTION: 3.2 168 hrs @ 38°C / 9	Adhesive Peel Strength 08% RH	ASTM D17:53CB-10-01	Specification 2.2 N/cm	<u>Results</u> 14.1	<u>Status</u> Pass
24 hrs	Adhesive Peel Strength @ 79°C @ 38°C / 95% RH @ -29°C	LP-463CB-10-01	Specification 2.2 N / cm	<u>Results</u> 3.8	<u>Status</u> Pass
SECTION: 3.3 Initial, 24 hrs @ RT	Shear Adhesion		Specification 55 kPa	<u>Results</u> 186.6	<u>Status</u> Pass
SECTION: 3.3 168 hrs @ 79°C	Shear Adhesion	LP-463CB-10-01	Specification 48 kPa	<u>Results</u> 470.7	<u>Status</u> Pass
SECTION: 3.3 168 hrs @ 38°C / 9	Shear Adhesion 98% RH	ASTM D1735	Specification 55 kPa	<u>Results</u> 200.8	<u>Status</u> Pass
24 hrs	Shear Adhesion @ 79°C @ 38°C / 95% RH @ -29°C	LP-463CB-10-01	<u>Specification</u> 55 kPa	<u>Results</u> 345.8	<u>Status</u> Pass

CERTIFIED BY:

ISSUE DATE:

1-1-24

Dave Nichols Jr, Automotive Lab Techniclan

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.