



250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 0910
SUPPORT: FELT
SUBSTRATE: ABS
CERT NO.: 230103 - 1034



FCA MS-JZ-8-22
OEM Rev Date: Dec 16
Anti-Squeak Fabric, Pressure Sensitive

TAPE REQUIREMENTS:

SECTION:	ASTM	Specification	Results	Status
SECTION: Wear Resistance Taber Abrasion, Dry, 1000 Cycles, CS-10, 1000 g Load	ASTM D3884	No Noticeable Wear or Adhesive / Fiber Loosening	Some Wear But No Fiber Loosening	Pass
Taber Abrasion, Wet, 1000 Cycles, CS-10, 500 g Load		No Noticeable Wear or Adhesive / Fiber Loosening	No Loosening of Fibers or Adhesive	Pass
SECTION: Odor Dry, 1 hr @ 79°C	ASTM J1351	No Disagreeable Odor	2 - Slight, But Noticeable Odor	Pass
Wet, 1 hr @ 79°C - Deionized Water		No Disagreeable Odor	1 - No Noticeable Odor	Pass
SECTION: Flammability Initial, Component	FMVSS 302	< 101.6 mm / min	< B 50	Pass
SECTION: Tape Tests A. Original, 20 mins @ RT, Tape Tests,	LP-463LB-19-01	No Adhesive Lifting	Good, Stable, No Lifting	Pass
B. 168 hours @ 110°C, Tape Tests,		No Adhesive Lifting	Good, Stable, No Lifting	Pass
C. Cycles (2X), Tape Tests, 16 hrs @ 38°C / 95% RH 24 hrs @ 110°C 6 hrs @ -29°C		No Adhesive Lifting	Good, Stable, No Lifting	Pass
D. Non-Condensing Humidity, 100 hrs @ 38°C / 95% RH, Tape Tests,		No Adhesive Lifting	Good, Stable, No Lifting	Pass
SECTION: Bond Peel Tests A. Original, 20 mins @ RT, Bond Peel Tests,	ASTM D1000	7 N / cm	13.4	Pass
B. 168 hours @ 110°C, Bond Peel Tests,		8 N / cm	14.5	Pass
C. Cycles (2X), Bond Peel Tests, 16 hrs @ 38°C / 95% RH 24 hrs @ 110°C 6 hrs @ -29°C		9.5 N / cm	15.6	Pass
D. Non-Condensing Humidity, 100 hrs @ 38°C / 95% RH, Bond Peel Te		9 N / cm	15.9	Pass
SECTION: Resistance to Non-Condensing Humidity Resistance to Non-Condensing Humidity	LP-463KB-12-01	No Fade, Color Changes or Loosening of Fibers	Not Tested	Not Tested
		<i>As Reported by Supplier</i>		
SECTION: Resistance to Crocking Wet / Dry Resistance to Crocking Wet	SAE J861	4 Min Rating	Not Tested	Not Tested
		<i>As Reported by Supplier</i>		
Resistance to Crocking Dry		4 Min Rating	Not Tested	Not Tested

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.