

250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

Fax: 888-358-4469

psa.tape@averydennison.com email:

URL: tapes.averydennison.com

## **TEST REPORT**

PRODUCT: FT 1126 SUPPORT: **EPDM FOAM** 

SUBSTRATE: SS

CERT NO .: 230103 - 1157

FCA PF-10770

OEM Rev Date: Feb 15

Adhesion - PSA, Cellular and Fibrous Materials

Table 2 Flexible Composites



TADE	REQUIRE	MENTO
IAFE	KEWUIKE	IVIEIVI 3.

Heat Resistance LP-463TB-03-01\* SECTION: 3.0

2.2, Heat Resistance, Initial, 2 hrs @ RT

SECTION: 3.0 Heat Resistance LP-463CB-10-01\*

2.2, Heat Resistance, 168 hrs @ 79°C

Heat Resistance LP-463CB-10-01\* SECTION: 3.0

2.2, Heat Resistance, 8 hrs @ 93°C"

SECTION: 3.0 **Heat Resistance** 

2.2, Heat Resistance, 24 hrs Water Immersion

SECTION: 3.0 Heat Resistance ASTM D1735

2.2, Heat Resistance, Cycles (5x)

24 hrs @ 79°C

24 hrs @ 38°C / 95% RH

24 hrs @ -29°C

**Specification** No Adhesion Loss or Lifting

**Specification** 

No Adhesion Loss or Lifting

**Specification** 

No Adhesion Loss or Lifting

## **Specification**

No Adhesion Loss or Lifting

## **Specification**

Specification

0.9 N/cm

**Specification** 

3.3 N/cm

**Specification** 

3.3 N/cm

**Specification** 

3.3 N/cm

**Specification** 

3.3 N/cm

No Adhesion Loss or Lifting

## Results

Stable, No Lift or Adhesion Loss

Results

Stable, No Lift or Adhesion Loss

**Results** 

Stable, No Lift or Adhesion Loss

Stable, No Lift or Adhesion Loss

Results

**Pass** 

**Status** 

**Pass** 

Status

**Pass** 

SECTION: 3.0 **Peel Adhesion** LP-463TB-03-01\*

3.0, Adhesion, Initial, 2 hrs @ RT

SECTION: 3.0 **Peel Adhesion** LP-463CB-10-01\*

3.0, Adhesion, 168 hrs @ 79°C

SECTION: 3.0 **Peel Adhesion** LP-463CB-10-01\*

3.0, Adhesion, 8 hrs @ 93°C

SECTION: 3.0 **Peel Adhesion** 3.0, Adhesion, 24 hr Water Immersion

SECTION: 3.0 **Peel Adhesion ASTM D1735** 

3.0, Adhesion, Heat Resistance, Cycles (5x)

24 hrs @ 79°C

24 hrs @ 38°C / 95% RH

24 hrs @ -29°C

**Pass** 

Results

**Pass** 

**Status** 

Status

**Pass** 

**Status** 

**Pass** 

Status

**Status** 

Stable, No Lift or Adhesion Loss

Results

Results

7.0

3.6

Results

**Status** 5.3 **Pass** 

Results

Status 8.8 **Pass** 

**Results** 3.6

**Status Pass** 

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-24

8-14-2017

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.