

250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

Fax: **888-358-4469** 

email: psa.tape@averydennison.com

URL: tapes.averydennison.com

## **TEST REPORT**

PRODUCT: FT 1158

SUPPORT: EPDM FOAM

SUBSTRATE: SS

CERT NO.: 230103 - 1201

FCA PF-10770

OEM Rev Date: Feb 15

Adhesion - PSA, Cellular and Fibrous Materials

**Specification** 

No Adhesion Loss or Lifting

Table 2 Flexible Composites



## **TAPE REQUIREMENTS:**

SECTION: 3.0 Heat Resistance LP-463TB-03-01\*

2.2, Heat Resistance, Initial, 2 hrs @ RT

SECTION: 3.0 Heat Resistance LP-463CB-10-01\*

2.2, Heat Resistance, 168 hrs @ 79°C

SECTION: 3.0 Heat Resistance LP-463CB-10-01\*

2.2, Heat Resistance, 8 hrs @ 93°C"

SECTION: 3.0 Heat Resistance

2.2, Heat Resistance, 24 hrs Water Immersion

SECTION: 3.0 Heat Resistance ASTM D1735

2.2, Heat Resistance, Cycles (5x)

24 hrs @ 79°C

24 hrs @ 38°C / 95% RH

24 hrs @ -29°C

SECTION: 3,0	Peel Adhesion	LP-463TB-03-01*

3.0, Adhesion, Initial, 2 hrs @ RT

SECTION: 3.0 Peel Adhesion LP-463CB-10-01\*

3.0, Adhesion, 168 hrs @ 79°C

SECTION: 3.0 Peel Adhesion LP-463CB-10-01\*

3.0, Adhesion, 8 hrs @ 93°C

SECTION: 3.0 Peel Adhesion

3.0, Adhesion, 24 hr Water Immersion

SECTION: 3.0 Peel Adhesion ASTM D1735

3.0, Adhesion, Heat Resistance, Cycles (5x)

24 hrs @ 79°C

24 hrs @ 38°C / 95% RH

24 hrs @ -29°C

Results

Stable, No Lift or Adhesion Loss

Results

Stable, No Lift or Adhesion Loss

**Results** 

Stable, No Lift or Adhesion Loss

<u>Results</u>

Stable, No Lift or Adhesion Loss

Results

Stable, No Lift or Adhesion Loss

Status

**Pass** 

**Status** 

**Pass** 

Status

**Pass** 

**Status** 

**Pass** 

**Status** 

**Pass** 

**Status** 

**Pass** 

**Pass** 

Specification Results
0.9 N/cm 7.9

<u>Specification</u> <u>Results</u> <u>Status</u>

**3.3 N / cm** 8.8 **Pass** 

 Specification
 Results
 Status

 3.3 N/cm
 8.8
 Pass

SpecificationResultsStatus3.3 N/cm7.6Pass

Specification Results Status

3.3 N/cm 8.8

Original Test Date:

**CERTIFIED BY:** 

Dave Nichols Jr. Automotive Lab Technician

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.