

250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

Fax: 888-358-4469

psa.tape@averydennison.com email:

URL: tapes.averydennison.com

TEST REPORT

PRODUCT: **HPA 1905 PET**

SUPPORT: NITRILE VINYL FOAM

SUBSTRATE: **ABS**

CERT NO .: 230103 - 1204

FCA PF-10770

OEM Rev Date: Feb 15

Adhesion - PSA, Cellular and Fibrous Materials

Table 2 Flexible Composites



TAPE REQUIREMENTS:

Heat Resistance LP-463TB-03-01* SECTION: 3.0

2.2, Heat Resistance, Initial, 2 hrs @ RT

SECTION: 3.0 Heat Resistance LP-463CB-10-01*

2.2, Heat Resistance, 168 hrs @ 79°C

Heat Resistance LP-463CB-10-01* SECTION: 3.0

2.2, Heat Resistance, 8 hrs @ 93°C"

SECTION: 3.0 **Heat Resistance**

2.2, Heat Resistance, 24 hrs Water Immersion

SECTION: 3.0 Heat Resistance ASTM D1735

2.2, Heat Resistance, Cycles (5x)

24 hrs @ 79°C 24 hrs @ 38°C / 95% RH

24 hrs @ -29°C

Specification

No Adhesion Loss or Lifting

Specification

Specification

0.9 N/cm

Specification

3.3 N/cm

Specification

3.3 N/cm

Specification

3.3 N/cm

Specification

3.3 N/cm

No Adhesion Loss or Lifting

Results

Results

Stable, No Lift or Adhesion Loss

Stable, No Lift or Adhesion Loss

Stable, No Lift or Adhesion Loss

Pass

SECTION: 3.0 **Peel Adhesion** 3.0, Adhesion, Initial, 2 hrs @ RT

LP-463TB-03-01*

Peel Adhesion LP-463CB-10-01*

3.0, Adhesion, 168 hrs @ 79°C

SECTION: 3.0

SECTION: 3.0 **Peel Adhesion** LP-463CB-10-01*

3.0, Adhesion, 8 hrs @ 93°C

SECTION: 3.0 **Peel Adhesion**

3.0, Adhesion, 24 hr Water Immersion

SECTION: 3.0 **Peel Adhesion ASTM D1735**

3.0, Adhesion, Heat Resistance, Cycles (5x)

24 hrs @ 79°C

24 hrs @ 38°C / 95% RH

24 hrs @ -29°C

Stable, No Lift or Adhesion Loss

ANSI National Accreditation Board

ACCREDITED

TESTING LABORATORY

Pass

Status

Pass

Status

Status

Results

Stable, No Lift or Adhesion Loss **Pass**

Results

Status Pass

Results

Status

Status

Pass

Results 9.4

Results Status

10.9

Pass

Results 12.2

Status Pass

Results 9.3

Status **Pass**

Results

Status

10.7

Pass

CERTIFIED BY:

Dave Nichols Jr. Automotive Lab Technician

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.