

250 Chester Street			
Painesville, Ohio 44077			
Phone:	866-GO-AVERY (866-462-8379)		
Fax:	888-358-4469		
email:	psa.tape@averydennison.com		
URL:	tapes.averydennison.com		

## **TEST REPORT**

Adhesion - PSA, Cellular and Fibrous Materials

PRODUCT: SUPPORT: SUBSTRATE: CERT NO.:

FCA PF-10770

OEM Rev Date: Feb 15

Table 2 Flexible Composites

**FT 702P EPDM FOAM E: E-COATED METAL** 230103 - 1154



TAPE REQUIREMENTS:SECTION: 3.0Heat ResistanceLP-463TB-03-01*2.2, Heat Resistance, Initial, 2 hrs @ RT	Specification	<u>Results</u>	<u>Status</u>
	No Adhesion Loss or Lifting	Stable, No Lift or Adhesion Loss	Pass
SECTION: <b>3.0</b> Heat Resistance LP-463CB-10-01*	Specification	<u>Results</u>	<u>Status</u>
2.2, Heat Resistance, 168 hrs @ 79°C	No Adhesion Loss or Lifting	Stable, No Lift or Adhesion Loss	Pass
SECTION: <b>3.0</b> Heat Resistance LP-463CB-10-01*	Specification	<u>Results</u>	<u>Status</u>
2.2, Heat Resistance, 8 hrs @ 93°C"	No Adhesion Loss or Lifting	Stable, No Lift or Adhesion Loss	Pass
SECTION: <b>3.0</b> Heat Resistance	Specification	<u>Results</u>	<u>Status</u>
2.2, Heat Resistance, 24 hrs Water Immersion	No Adhesion Loss or Lifting	Stable, No Lift or Adhesion Loss	Pass
SECTION: 3.0 Heat Resistance ASTM D1735   2.2, Heat Resistance, Cycles (5x) 72 hrs @ 70°C 24 hrs @ 38°C / 95% RH   24 hrs @ -29°C 29°C 29°C	Specification	<u>Results</u>	<u>Status</u>
	No Adhesion Loss or Lifting	Stable, No Lift or Adhesion Loss	Pass
SECTION: 3.0 Peel Adhesion LP-463TB-03-01*	Specification	Results	<u>Status</u>
3.0, Adhesion, Initial, 2 hrs @ RT	0.9 N / cm	4.7	Pass
SECTION: 3.0 Peel Adhesion LP-463CB-10-01*   3.0, Adhesion, 168 hrs @ 79°C	Specification	<u>Results</u>	<u>Status</u>
	3.3 N / cm	9.5	Pass
SECTION: 3.0 Peel Adhesion LP-463CB-10-01*   3.0, Adhesion, 8 hrs @ 93°C	Specification	Results	<u>Status</u>
	3.3 N / cm	5.7	Pass
SECTION: 3.0Peel Adhesion3.0, Adhesion, 24 hr Water Immersion	Specification	Results	<u>Status</u>
	3.3 N / cm	3.7	Pass
SECTION: 3.0 Peel Adhesion ASTM D1735 3.0, Adhesion, Heat Resistance, Cycles (5x) 72 hrs @ 70°C 24 hrs @ 38°C / 95% RH 24 hrs @ -29°C	Specification 3.3 N / cm	<u>Results</u> 5.7	<u>Status</u> Pass

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience. This laboratory is not accredited for the calibrations or tests marked \*.

rmanaa Tanaa 250 Chaster St. Dainaavilla Ohia 44077

Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077

Original Test Date:

ISSUE DATE:

1-1-24

8-14-2017