

250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

Fax: 888-358-4469

psa.tape@averydennison.com email:

URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT B 12 PT BD SUPPORT: **EPDM FOAM**

SUBSTRATE: SS

CERT NO.: 230103 - 1144

FCA PF-10770

OEM Rev Date: Feb 15

Adhesion - PSA, Cellular and Fibrous Materials

Specification

No Adhesion Loss or Lifting

Specification

No Adhesion Loss or Lifting

Table 2 Flexible Composites



т	۸D	DE	\cap	IREN	/EN	TQ.
	AΡ	ᄄ	wu	IKEN	/IEN	13:

SECTION: 3.0 Heat Resistance LP-463TB-03-01*

2.2, Heat Resistance, Initial, 2 hrs @ RT

SECTION: 3.0 Heat Resistance LP-463CB-10-01*

2.2, Heat Resistance, 168 hrs @ 79°C

SECTION: 3.0 Hea

2.2, Heat Resistance, 8

SECTION: 3.0 **Heat Resistance**

2.2, Heat Resistance, 24 hrs Water Immersion

SECTION: 3.0 Heat Resistance ASTM D1735

2.2, Heat Resistance, Cycles (5x)

24 hrs @ 79°C

24 hrs @ 38°C / 95% RH

24 hrs @ -29°C

eat Resistance LP-463CB-10-01*	Specification	<u>Results</u>	Statu
8 hrs @ 93°C"	No Adhesion Loss or Lifting	Stable, No Lift or Adhesion Loss	Pass

Specification No Adhesion Loss or Lifting

Specification

No Adhesion Loss or Lifting

<u>tus</u> SS

Status

Pass

Status

Pass

Pass

Results Status

Stable, No Lift or Adhesion Loss **Pass**

> Results **Status Pass**

Stable, No Lift or Adhesion Loss

Results

Stable, No Lift or Adhesion Loss

Results

Stable, No Lift or Adhesion Loss

SECTION: 3.0 **Peel Adhesion** LP-463TB-03-01* Specification Results Status 0.9 N/cm 16.4 3.0, Adhesion, Initial, 2 hrs @ RT **Pass**

SECTION: 3.0 **Peel Adhesion** LP-463CB-10-01* **Specification** Results Status **Pass**

3.0, Adhesion, 168 hrs @ 79°C 3.3 N/cm 10.5

SECTION: 3.0 **Peel Adhesion** LP-463CB-10-01* **Specification** Results **Status** 3.0, Adhesion, 8 hrs @ 93°C 3.3 N/cm 10.5 **Pass**

SECTION: 3.0 **Peel Adhesion** Specification Results Status 3.0, Adhesion, 24 hr Water Immersion 3.3 N/cm 5.1 **Pass**

SECTION: 3.0 **Peel Adhesion ASTM D1735 Specification Results Status** 10.8 3.3 N/cm

3.0, Adhesion, Heat Resistance, Cycles (5x)

Adhesion, Heat Resistance, Cycles (5x)

24 hrs @ 79°C

24 hrs @ 38°C / 95% RH

24 hrs @ -29°C

ISSUE DATE: 1-1-24

CERTIFIED BY:

Dave Nichols Jr. Automotive Lab Technician

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.