

250 Chester Street Painesville, Ohio 44077 Phone: 866-GO-AVERY (866-462-8379) Fax: 888-358-4469 psa.tape@averydennison.com email: URL: tapes.averydennison.com

TEST REPORT

PRODUCT: SUPPORT: SUBSTRATE: CERT NO .:

FCA PF-10770

OEM Rev Date: Feb 15

Table 2 Flexible Composites

FT B 12 PT BD NITRILE VINYL FOAM E-COATED METAL 230103 - 1144

Adhesion - PSA, Cellular and Fibrous Materials



Status

Pass

Status

Pass

Status

Pass

Status

Pass

Status

Pass

Status

Pass

Status

Pass

Status

Pass

Status

Pass

Status

Pass

TAPE REQUIREMENTS:SECTION: 3.0Heat Resistance2.2, Heat Resistance, Initial, 2 hrs @ R		Specification No Adhesion Loss or Lifting	<u>Results</u> Stable, No Lift or Adhesion Loss
SECTION: 3.0 Heat Resistance	LP-463CB-10-01*	Specification	<u>Results</u>
2.2, Heat Resistance, 168 hrs @ 79°C		No Adhesion Loss or Lifting	Stable, No Lift or Adhesion Loss
SECTION: 3.0 Heat Resistance	LP-463CB-10-01*	Specification	<u>Results</u>
2.2, Heat Resistance, 8 hrs @ 93°C"		No Adhesion Loss or Lifting	Stable, No Lift or Adhesion Loss
SECTION: 3.0 Heat Resistance	nersion	Specification	<u>Results</u>
2.2, Heat Resistance, 24 hrs Water Imr		No Adhesion Loss or Lifting	Stable, No Lift or Adhesion Loss
SECTION: 3.0 Heat Resistance 2.2, Heat Resistance, Cycles (5x) 24 hrs @ 79°C 24 hrs @ 38°C / 95° 24 hrs @ -29°C		Specification No Adhesion Loss or Lifting	<u>Results</u> Stable, No Lift or Adhesion Loss
SECTION: 3.0 Peel Adhesion 3.0, Adhesion, Initial, 2 hrs @ RT	LP-463-TB-03-01*	Specification 0.9 N / cm	<u>Results</u> 11.9
SECTION: 3.0 Peel Adhesion	LP-463-CB-10-01*	Specification	Results
3.0, Adhesion, 168 hrs @ 79°C		3.3 N / cm	11.3
SECTION: 3.0 Peel Adhesion	LP-463-CB-10-01*	Specification	<u>Results</u>

SECTION: 3.0 **Peel Adhesion** 3.0, Adhesion, 24 hr Water Immersion

3.0, Adhesion, 8 hrs @ 93°C

SECTION: 3.0 **Peel Adhesion** ASTM D1735 3.0, Adhesion, Heat Resistance, Cycles (5x) Adhesion, Heat Resistance, Cycles (5x) 24 hrs @ 79°C 24 hrs @ 38°C / 95% RH 24 hrs @ -29°C

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience. This laboratory is not accredited for the calibrations or tests marked *.

3.3 N/cm

Specification

3.3 N/cm

Specification

3.3 N/cm

Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077

Original Test Date:

ISSUE DATE:

1-1-24

8-14-2017

10.7

Results

11.6

Results

10.1