## **TEST REPORT**



250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

Fax: 888-358-4469

email: psa.tape@averydennison.com
URL: tapes.averydennison.com

PRODUCT: FT 1126 12 PT BD
SUPPORT: 4.8 MM PORON FOAM
SUBSTRATE: TPE

SUBSTRATE: TPE CERT NO.: 230103 - 1107

FCA PF.90175

OEM Rev Date: Jun 17 Pressure Sensitive Adhesives Includes Chrysler Standard PF-10770 Table 2 Flexible Composites



TAPE REQUIREME	N	T	S	:
OFOTION O				ı

SECTION: 3.0 2.2, Heat Resistar	Heat Resistance nce, Initial, 2 hrs @ R		Specification No Adhesion Loss or Lifting	Results Good, Stable, No Staining or Removal	Status Pass
SECTION: <b>3.0</b> 2.2, Heat Resistar	Heat Resistance nce, 168 hrs @ 79°C	LP-463-CB-10-01*	No Adhesion Loss or Lifting	Good, Stable, No Staining or Removal	Pass
SECTION: <b>3.0</b> 2.2, Heat Resistar	Heat Resistance nce, 8 hrs @ 93°C"	LP-463-CB-10-01*	No Adhesion Loss or Lifting	Good, Stable, No Staining or Removal	Pass
SECTION: <b>3.0</b> 2.2, Heat Resistar	Heat Resistance nce, 24 hrs Water Imr	mersion	No Adhesion Loss or Lifting	Good, Stable, No Staining or Removal	Pass
SECTION: 3.0 2.2, Heat Resistar	Heat Resistance nce, Cycles (5x) 72 hrs @ 70°C 24 hrs @ 38°C / 95 24 hrs @ -29°C		No Adhesion Loss or Lifting	Good, Stable, No Staining or Removal	Pass
SECTION: <b>3.0</b> 3.0, Adhesion, Init	Peel Adhesion ial, 2 hrs @ RT	LP-463-TB-03-01*	Specification 0.9 N / cm	Results 5.5	Status Pass
SECTION: <b>3.0</b> 3.0, Adhesion, 168	Peel Adhesion 3 hrs @ 79°C	LP-463-CB-10-01*	3.3 N/cm	5.4	Pass
SECTION: 3.0 3.0, Adhesion, 8 h	Peel Adhesion rs @ 93°C	LP-463-CB-10-01*	3.3 N/cm	5.0	Pass
SECTION: 3.0 3.0, Adhesion, 24	<b>Peel Adhesion</b> hr Water Immersion		3.3 N / cm	6.2	Pass
SECTION: <b>3.0</b> 3.0, Adhesion, He	Peel Adhesion at Resistance, Cyclet Adhesion, Heat Res 72 hrs @ 70°C 24 hrs @ 38°C / 95	sistance, Cycles (5x)	3.3 N/cm	6.2	Pass

**CERTIFIED BY:** 

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.