

250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

Fax: 888-358-4469

email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 1126 12 PT BD SUPPORT: EPDM FOAM

SUBSTRATE: SS

CERT NO.: 230103 - 1101

FCA PF.90175

OEM Rev Date: Mar 15
Pressure Sensitive Adhesives
Includes Chrysler Standard PF-10770

Table 2 Flexible Composites

ANSI National Accreditation Board

A C C R E D I T E D

ISO/IEC I7025

TESTING LABORATORY

TAPE REQUIREMENTS:

SECTION: **3.0 Heat Resistance** 2.2, Heat Resistance, Initial, 2 hrs @ RT

SECTION: **3.0** Heat Resistance 2.2, Heat Resistance, 168 hrs @ 79°C

SECTION: **3.0** Heat Resistance 2.2, Heat Resistance, 8 hrs @ 93°C"

SECTION: 3.0 Heat Resistance

2.2, Heat Resistance, 24 hrs Water Immersion

SECTION: **3.0 Heat Resistance** 2.2, Heat Resistance, Cycles (5x)

72 hrs @ 70°C 24 hrs @ 38°C / 95% RH

24 hrs @ -29°C

Specification

No Adhesion Loss or Lifting

Specification

Specification

0.9 N/cm

Specification

3.3 N/cm

Specification

3.3 N/cm

Specification

3.3 N/cm

Specification

3.3 N/cm

No Adhesion Loss or Lifting

Results

Stable, No Lift or Adhesion Loss

Results

Stable, No Lift or Adhesion Loss

Results

Stable, No Lift or Adhesion Loss

Results

Stable, No Lift or Adhesion Loss

Results

Stable, No Lift or Adhesion Loss

Pass

Status

Pass

Status

Pass

Status

Pass

Status

Pass

Status

Status

Pass

Status

Pass

Status

Pass

Status

Pass

SECTION: 3.0 Peel Adhesion

3.0, Adhesion, Initial, 2 hrs @ RT

SECTION: **3.0** Peel Adhesion 3.0, Adhesion, 168 hrs @ 79°C

SECTION: 3.0 Peel Adhesion

3.0, Adhesion, 8 hrs @ 93°C

SECTION: **3.0** Peel Adhesion 3.0, Adhesion, 24 hr Water Immersion

SECTION: **3.0** Peel Adhesion 3.0, Adhesion, Heat Resistance, Cycles (5x)

Adhesion, Heat Resistance, Cycles (5x)

72 hrs @ 70°C

24 hrs @ 38°C / 95% RH

Results 7.0

Results

3.6

Results

5.3

Results

8.8

Results 3.6 Status Pass

CERTIFIED BY:

Dave Nichols Jr. Automotive Lab Technician

ISSUE DATE: 1-1-24

7-11-2017

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

250 Chester Street

250 Chester Street