

250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

Fax: 888-358-4469

psa.tape@averydennison.com email: URL:

tapes.averydennison.com

## **TEST REPORT**

PRODUCT: FT 1126 SUPPORT: **EPDM FOAM** 

SUBSTRATE: SS

CERT NO .: 230104 - 1115

FCA PF.90175

OEM Rev Date: Mar 15 Pressure Sensitive Adhesives

Includes Chrysler Standard PF-10770

Table 2 Flexible Composites

ANSI National Accreditation Board ACCREDITED TESTING LABORATORY

**TAPE REQUIREMENTS:** 

SECTION: 3.0 **Heat Resistance** 2.2, Heat Resistance, Initial, 2 hrs @ RT

SECTION: 3.0 **Heat Resistance** 2.2, Heat Resistance, 168 hrs @ 79°C

SECTION: 3.0 **Heat Resistance** 2.2, Heat Resistance, 8 hrs @ 93°C"

SECTION: 3.0 **Heat Resistance** 2.2, Heat Resistance, 24 hrs Water Immersion

SECTION: 3.0 **Heat Resistance** 

2.2, Heat Resistance, Cycles (5x)

72 hrs @ 70°C 24 hrs @ 38°C / 95% RH

24 hrs @ -29°C

**Specification** 

No Adhesion Loss or Lifting

Results

Stable, No Lift or Adhesion Loss

Results

Stable, No Lift or Adhesion Loss

Stable, No Lift or Adhesion Loss

Stable, No Lift or Adhesion Loss

SECTION: 3.0 **Peel Adhesion** 3.0, Adhesion, Initial, 2 hrs @ RT

SECTION: 3.0 **Peel Adhesion** 3.0, Adhesion, 168 hrs @ 79°C

SECTION: 3.0 **Peel Adhesion** 

3.0, Adhesion, 8 hrs @ 93°C

SECTION: 3.0 **Peel Adhesion** 

3.0, Adhesion, 24 hr Water Immersion

**Peel Adhesion** 3.0, Adhesion, Heat Resistance, Cycles (5x)

Adhesion, Heat Resistance, Cycles (5x)

72 hrs @ 70°C

24 hrs @ 38°C / 95% RH

Stable, No Lift or Adhesion Loss

**Results** 

Results

**Pass** 

Results

**Status Pass** 

Status

**Pass** 

**Status** 

**Pass** 

Status

**Pass** 

**Status** 

Specification Results **Status** 0.9 N/cm 7.0 **Pass** 

**Specification** Results Status

3.3 N/cm 3.6 **Pass** 

**Results Specification Status** 3.3 N/cm 5.3 **Pass** 

**Specification** Results Status 3.3 N/cm 8.8 **Pass** 

**Specification** 

**Results Status** 3.6 3.3 N/cm **Pass** 

CERTIFIED BY:

SECTION: 3.0

Dave Nichols Jr. Automotive Lab Technician

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

Original Test Date: