	VERY
--	------

250 Chester Street Painesville, Ohio 44077 Phone: 866-GO-AVERY (866-462-8379) Fax: 888-358-4469 email: psa.tape@averydennison.com URL: tapes.averydennison.com

TEST REPORT

SUBSTRATE:

PRODUCT:

SUPPORT:

CERT NO .:

FT 3043 **EPDM FOAM** TPE 230103 - 1122



FCA PF.90175 OEM Rev Date: Jun 17 Pressure Sensitive Adhesives Includes Chrysler Standard PF-10770 Table 2 Flexible Composites

TAPE REQUIREMENTS:SECTION: 3.0Heat ResistanceLP-463-TB-03-01*2.2, Heat Resistance, Initial, 2 hrs @ RT	Specification No Adhesion Loss or Lifting	<u>Results</u> Stable, No Lift or Adhesion Loss	<u>Status</u> Pass
SECTION: 3.0 Heat Resistance LP-463-CB-10-01* 2.2, Heat Resistance, 168 hrs @ 79°C	No Adhesion Loss or Lifting	Stable, No Lift or Adhesion Loss	Pass
SECTION: 3.0 Heat Resistance LP-463-CB-10-01* 2.2, Heat Resistance, 8 hrs @ 93°C"	No Adhesion Loss or Lifting	Stable, No Lift or Adhesion Loss	Pass
SECTION: 3.0 Heat Resistance 2.2, Heat Resistance, 24 hrs Water Immersion	No Adhesion Loss or Lifting	Stable, No Lift or Adhesion Loss	Pass
SECTION: 3.0 Heat Resistance ASTM D1735 2.2, Heat Resistance, Cycles (5x) 72 hrs @ 70°C 24 hrs @ 38°C / 95% RH 24 hrs @ -29°C	No Adhesion Loss or Lifting	Stable, No Lift or Adhesion Loss	Pass
SECTION: 3.0 Peel Adhesion LP-463-TB-03-01* 3.0, Adhesion, Initial, 2 hrs @ RT	Specification 0.9 N / cm	<u>Results</u> 8.3	<u>Status</u> Pass
SECTION: 3.0 Peel Adhesion LP-463-CB-10-01* 3.0, Adhesion, 168 hrs @ 79°C	3.3 N / cm	7.9	Pass
SECTION: 3.0 Peel Adhesion LP-463-CB-10-01* 3.0, Adhesion, 8 hrs @ 93°C	3.3 N / cm	7.1	Pass
SECTION: 3.0 Peel Adhesion 3.0, Adhesion, 24 hr Water Immersion	3.3 N / cm	8.1	Pass
SECTION: 3.0 Peel Adhesion ASTM D1735 3.0, Adhesion, Heat Resistance, Cycles (5x) Adhesion, Heat Resistance, Cycles (5x) 72 hrs @ 70°C 24 hrs @ 38°C / 95% RH	3.3 N / cm	7.2	Pass

CERTIFIED BY:

ISSUE DATE:

1-1-24

Dave Nichols Jr, Automotive Lab Technician

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *. Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077

Original Test Date: 8-9-2018 Page 1 of 1