



250 Chester Street  
 Painesville, Ohio 44077  
 Phone: 866-GO-AVERY (866-462-8379)  
 Fax: 888-358-4469  
 email: psa.tape@averydennison.com  
 URL: tapes.averydennison.com

**TEST REPORT**

PRODUCT: FT 8217  
 SUPPORT: NITRILE VINYL FOAM  
 SUBSTRATE: SS  
 CERT NO.: 230103 - 1124



**FCA PF.90175**  
 OEM Rev Date: Mar 15  
 Pressure Sensitive Adhesives  
 Includes Chrysler Standard PF-10770  
 Table 2 Flexible Composites

**TAPE REQUIREMENTS:**

| SECTION:  | Specification               | Results                          | Status |
|---|-----------------------------|----------------------------------|--------|
| 3.0 Heat Resistance<br>2.2, Heat Resistance, Initial, 2 hrs @ RT  | No Adhesion Loss or Lifting | Stable, No Lift or Adhesion Loss | Pass   |
| 3.0 Heat Resistance<br>2.2, Heat Resistance, 168 hrs @ 79°C   | No Adhesion Loss or Lifting | Stable, No Lift or Adhesion Loss | Pass   |
| 3.0 Heat Resistance<br>2.2, Heat Resistance, 8 hrs @ 93°C   | No Adhesion Loss or Lifting | Stable, No Lift or Adhesion Loss | Pass   |
| 3.0 Heat Resistance<br>2.2, Heat Resistance, 24 hrs Water Immersion   | No Adhesion Loss or Lifting | Stable, No Lift or Adhesion Loss | Pass   |
| 3.0 Heat Resistance<br>2.2, Heat Resistance, Cycles (5x)<br>72 hrs @ 70°C<br>24 hrs @ 38°C / 95% RH<br>24 hrs @ -29°C                                 | No Adhesion Loss or Lifting | Stable, No Lift or Adhesion Loss | Pass   |
| 3.0 Peel Adhesion<br>3.0, Adhesion, Initial, 2 hrs @ RT   | 0.9 N / cm                  | 17.8                             | Pass   |
| 3.0 Peel Adhesion<br>3.0, Adhesion, 168 hrs @ 79°C  | 3.3 N / cm                  | 18.0                             | Pass   |
| 3.0 Peel Adhesion<br>3.0, Adhesion, 8 hrs @ 93°C  | 3.3 N / cm                  | 15.8                             | Pass   |
| 3.0 Peel Adhesion<br>3.0, Adhesion, 24 hr Water Immersion   | 3.3 N / cm                  | 3.3                              | Pass   |
| 3.0 Peel Adhesion<br>3.0, Adhesion, Heat Resistance, Cycles (5x)<br>Adhesion, Heat Resistance, Cycles (5x)<br>72 hrs @ 70°C<br>24 hrs @ 38°C / 95% RH | 3.3 N / cm                  | 16.5                             | Pass   |

CERTIFIED BY:   
 Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request  
 This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.  
 Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.