

250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

Fax: 888-358-4469

email: psa.tape@averydennison.com
URL: tapes.averydennison.com

PRODUCT: FBA 8960

**TEST REPORT** 

SUPPORT: PET FOAM SUBSTRATE: ABS

CERT NO.: 230103 - 1137

FCA PF.90175

OEM Rev Date: Mar 15
Pressure Sensitive Adhesives

Includes Chrysler Standard PF-10770

Table 2 Flexible Composites

ANSI National Accreditation Board

A C C R E D I T E D

SOJECTORS

TESTING LABORATORY

**TAPE REQUIREMENTS:** 

SECTION: **3.0 Heat Resistance** 2.2, Heat Resistance, Initial, 2 hrs @ RT

SECTION: 3.0 Heat Resistance

2.2, Heat Resistance, 168 hrs @ 79°C

SECTION: **3.0** Heat Resistance 2.2, Heat Resistance, 8 hrs @ 93°C"

SECTION: 3.0 Heat Resistance

2.2, Heat Resistance, 24 hrs Water Immersion

SECTION: 3.0 Heat Resistance

2.2, Heat Resistance, Cycles (5x)

72 hrs @ 70°C 24 hrs @ 38°C / 95% RH

24 hrs @ -29°C

Specification

No Adhesion Loss or Lifting

Specification

No Adhesion Loss or Lifting

**Specification** 

No Adhesion Loss or Lifting

**Specification** 

No Adhesion Loss or Lifting

Specification

Specification

0.9 N/cm

**Specification** 

3.3 N/cm

**Specification** 

3.3 N/cm

**Specification** 

3.3 N/cm

**Specification** 

3.3 N/cm

No Adhesion Loss or Lifting

Results

Stable, No Lift or Adhesion Loss

Results

Stable, No Lift or Adhesion Loss

**Results** 

Stable, No Lift or Adhesion Loss

Results

Stable, No Lift or Adhesion Loss

Results

Stable, No Lift or Adhesion Loss

Status Pass

**Status** 

**Pass** 

Status

**Pass** 

**Status** 

**Pass** 

Status

**Pass** 

**Status** 

**Pass** 

Status

**Pass** 

**Status** 

**Pass** 

SECTION: **3.0** Peel Adhesion 3.0, Adhesion, Initial, 2 hrs @ RT

SECTION: 3.0 Peel Adhesion

SECTION: 3.0 Peel Adhesion

3.0, Adhesion, 8 hrs @ 93°C

3.0, Adhesion, 168 hrs @ 79°C

SECTION: 3.0 Peel Adhesion

3.0, Adhesion, 24 hr Water Immersion

SECTION: **3.0** Peel Adhesion 3.0, Adhesion, Heat Resistance, Cycles (5x)

Adhesion, Heat Resistance, Cycles (5x)

72 hrs @ 70°C

24 hrs @ 38°C / 95% RH

Results 11.6

Results

16.3

Results

11.9

Results
11.2 Status
Pass

Results 16.0

<u>Status</u> Pass

**CERTIFIED BY:** 

Dave Nichols Jr. Automotive Lab Technician

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

Original Test Date: