

250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

Fax: 888-358-4469

psa.tape@averydennison.com email: URL: tapes.averydennison.com

**TEST REPORT** 

PRODUCT: FBA 8960 SUPPORT: **PVC FOAM** 

SUBSTRATE: **ABS** CERT NO.: 230103 - 1137

FCA PF.90175

OEM Rev Date: Mar 15 Pressure Sensitive Adhesives Includes Chrysler Standard PF-10770

Table 2 Flexible Composites



**TAPE REQUIREMENTS:** 

SECTION: 3.0 **Heat Resistance** 2.2, Heat Resistance, Initial, 2 hrs @ RT

SECTION: 3.0 **Heat Resistance** 2.2, Heat Resistance, 168 hrs @ 79°C

SECTION: 3.0 **Heat Resistance** 2.2, Heat Resistance, 8 hrs @ 93°C"

SECTION: 3.0 **Heat Resistance** 

2.2, Heat Resistance, 24 hrs Water Immersion

SECTION: 3.0 **Heat Resistance** 2.2, Heat Resistance, Cycles (5x)

> 72 hrs @ 70°C 24 hrs @ 38°C / 95% RH

24 hrs @ -29°C

Specification

No Adhesion Loss or Lifting

**Specification** 

Specification

0.9 N/cm

**Specification** 

3.3 N/cm

**Specification** 

3.3 N/cm

**Specification** 

3.3 N/cm

**Specification** 

3.3 N/cm

No Adhesion Loss or Lifting

Results

Stable, No Lift or Adhesion Loss

Results

Stable, No Lift or Adhesion Loss

**Results** 

Stable, No Lift or Adhesion Loss

Results

Stable, No Lift or Adhesion Loss

Results

Stable, No Lift or Adhesion Loss

**Status Pass** 

Status

**Pass** 

**Status** 

**Pass** 

Status

**Pass** 

**Status** 

**Pass** 

**Status** 

**Pass** 

Status

**Pass** 

**Status** 

**Pass** 

Status

SECTION: 3.0 **Peel Adhesion** 3.0, Adhesion, Initial, 2 hrs @ RT

SECTION: 3.0 **Peel Adhesion** 3.0, Adhesion, 168 hrs @ 79°C

SECTION: 3.0 **Peel Adhesion** 

3.0, Adhesion, 8 hrs @ 93°C

SECTION: 3.0 **Peel Adhesion** 

3.0, Adhesion, 24 hr Water Immersion

SECTION: 3.0 **Peel Adhesion** 3.0, Adhesion, Heat Resistance, Cycles (5x)

Adhesion, Heat Resistance, Cycles (5x)

72 hrs @ 70°C

24 hrs @ 38°C / 95% RH

Results 4.5

Results

6.2

Results 4.7

Results

5.3

**Results** 

**Pass** 

**Status** 6.6 **Pass** 

CERTIFIED BY:

Dave Nichols Jr. Automotive Lab Technician

ISSUE DATE: 1-1-24

Original Test Date:

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.