

250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

Fax: 888-358-4469

psa.tape@averydennison.com email: URL: tapes.averydennison.com

PRODUCT: FT B EZ

SUPPORT: NITRILE VINYL FOAM

TEST REPORT

SUBSTRATE: SS

CERT NO.: 230103 - 1047

FCA PF.90175

OEM Rev Date: Mar 15 Pressure Sensitive Adhesives

Includes Chrysler Standard PF-10770

Table 2 Flexible Composites

ACCREDITED TESTING LABORATORY

TAPE REQUIREMENTS:

SECTION: 3.0 **Heat Resistance** 2.2, Heat Resistance, Initial, 2 hrs @ RT

SECTION: 3.0 **Heat Resistance**

2.2, Heat Resistance, 168 hrs @ 79°C

SECTION: 3.0 **Heat Resistance** 2.2, Heat Resistance, 8 hrs @ 93°C"

SECTION: 3.0 **Heat Resistance**

2.2, Heat Resistance, 24 hrs Water Immersion

SECTION: 3.0 **Heat Resistance**

2.2, Heat Resistance, Cycles (5x)

72 hrs @ 70°C 24 hrs @ 38°C / 95% RH

24 hrs @ -29°C

Peel Adhesion

Specification

No Adhesion Loss or Lifting

Specification

No Adhesion Loss or Lifting

Specification

0.9 N/cm

Specification

3.3 N/cm

Specification

3.3 N/cm

Specification

3.3 N/cm

Specification

3.3 N/cm

Results

Stable, No Lift or Adhesion Loss

Results

Stable, No Lift or Adhesion Loss

Results

Stable, No Lift or Adhesion Loss

Results

Stable, No Lift or Adhesion Loss

Results

Stable, No Lift or Adhesion Loss

Status Pass

Status

Pass

Status

Pass

Status

Pass

Status

Status

Pass

Status

Pass

Status

Pass

Status

Pass

SECTION: 3.0 **Peel Adhesion** 3.0, Adhesion, Initial, 2 hrs @ RT

3.0, Adhesion, 168 hrs @ 79°C

SECTION: 3.0

SECTION: 3.0 **Peel Adhesion**

3.0, Adhesion, 8 hrs @ 93°C

SECTION: 3.0 **Peel Adhesion**

3.0, Adhesion, 24 hr Water Immersion

SECTION: 3.0 **Peel Adhesion** 3.0, Adhesion, Heat Resistance, Cycles (5x)

Adhesion, Heat Resistance, Cycles (5x)

72 hrs @ 70°C

24 hrs @ 38°C / 95% RH

Results

12.6

Results

11.7

Results

10.9

Results

Status 4.1 **Pass**

Results

11.2 **Pass**

CERTIFIED BY:

Dave Nichols Jr. Automotive Lab Technician

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.