

250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

Fax: 888-358-4469

email: psa.tape@averydennison.com
URL: tapes.averydennison.com

## **TEST REPORT**

PRODUCT: FT 1270 SUPPORT: PEU FOAM

SUBSTRATE: PP

CERT NO.: 221209 - 0915

FORD ESA-M11P19-A

OEM Rev Date: Dec 13 Adhesion Requirements

Polyurethane Foam to Polypropylene - Pressure Sensitive Film



**TAPE REQUIREMENTS:** 

3 Standard Requirements for Production Materials				
SECTION 3.1 Peel Strength, Plastic Membrane to Panel	<b>Specification</b>	ASTM D903	<u>Results</u>	<u>Status</u>
3.1.1, As Received	0.44 N/mm		0.81	Pass

SECTION 3.1	Peel Strength, Plastic Membrane to Panel	<u>Specification</u>	ASTM D903	<u>Results</u>	<u>Status</u>
3.1.2, Aged, Heat	Aged, 7 days @ 88°C	0.44 N / mm		0.75	Pass

SPEC:	3.1	Peel Strength, Plastic Membrane to Panel	<b>Specification</b>	ASTM D903	<u>Results</u>	<u>Status</u>
3.1.2. Hu	umidity.	7 davs @ 37°C / 95% RH	0.44 N/mm		0.89	Pass

SECTION 3.2	Peel Strength, Foam to Plastic Membrane	<u>Specification</u>	ASTM D903	<u>Results</u>	<u>Status</u>
3.2.1, Foam to PI	lastic Membrane, As Received	No Delamination		NA	NA

SECTION 3.3 Bond Separation	Specification ASTM D1000	Results	<u>Status</u>
3.3, 200 gram load, 1 hr @ RT	No Separation of Bond From an Actual	NT	Not Tested
	Production Part		

**CERTIFIED BY:** 

ISSUE DATE: <u>1-1-24</u>

Page 1 of 1

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

Jake Cowdrick, Automotive Application Specialist