

TEST REPORT

PRODUCT:	FT 7512
SUPPORT:	PET FOAM
SUBSTRATE:	ABS
CERT NO.:	221209 - 0915



250 Chester StreetPainesville, Ohio 44077Phone:866-GO-AVERY (866-462-8379)Fax:888-358-4469email:psa.tape@averydennison.comURL:tapes.averydennison.com

FORD ESA-M11P19-A OEM Rev Date: Dec 13 Adhesion Requirements Polyurethane Foam to Polypropylene - Pressure Sensitive Film

TAPE REQUIREMENTS:

Standard Requirements for Production Materials SECTION 3.1 Peel Strength, Plastic Membrane to Panel 3.1.1, As Received	Specification 0.44 N / mm	ASTM D903	<u>Results</u> 0.81	<u>Status</u> Pass
SECTION 3.1 Peel Strength, Plastic Membrane to Panel 3.1.2, Aged, Heat Aged, 7 days @ 88°C	Specification 0.44 N / mm	ASTM D903	<u>Results</u> 1.15	<u>Status</u> Pass
SPEC: 3.1 Peel Strength, Plastic Membrane to Panel 3.1.2, Humidity, 7 days @ 37°C / 95% RH	Specification 0.44 N / mm	ASTM D903	<u>Results</u> 1.10	<u>Status</u> Pass
SECTION 3.2 Peel Strength, Foam to Plastic Membrane 3.2.1, Foam to Plastic Membrane, As Received	Specification No Delamination	ASTM D903	<u>Results</u> NA	<u>Status</u> NA

SECTION 3.3 Bond Separation	Specification ASTM D100	0 <u>Results</u>	<u>Status</u>
3.3, 200 gram load, 1 hr @ RT	No Separation of Bond From an Actual	NT	Not Tested
	Production Part		

CERTIFIED BY:

Jake Cowdrick, Automotive Application Specialist

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience. This laboratory is not accredited for the calibrations or tests marked *.

Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077

Original Test Date: 6-1

6-16-2015 Page 1 of 1