

250 Chester Street Painesville, Ohio 44077

866-GO-AVERY (866-462-8379) Phone:

Fax: 888-358-4469

email: psa.tape@averydennison.com URL: tapes.averydennison.com

Standard Requirements for Production Materials

TEST REPORT

PRODUCT: FT 7515 SUPPORT: **PET FOAM**

SUBSTRATE: ABS

221209 - 0915 CERT NO.:

FORD ESA-M11P19-A

OEM Rev Date: Dec 13 Adhesion Requirements

Polyurethane Foam to Polypropylene - Pressure Sensitive Film



TADE	DEAL	IRFMF	MTC.
IAPE	REGU	IRFIVIE	N 1 3

3

SECTION 3.1 Peel Strength, Plastic Membrane to Panel 3.1.1, As Received	Specification 0.44 N/mm	ASTM D903	Results 0.96	<u>Status</u> Pass
SECTION 3.1 Peel Strength, Plastic Membrane to Panel 3.1.2, Aged, Heat Aged, 7 days @ 88°C	Specification 0.44 N/mm	ASTM D903	<u>Results</u> 1.31	Status Pass
SPEC: 3.1 Peel Strength, Plastic Membrane to Panel 3.1.2, Humidity, 7 days @ 37°C / 95% RH	Specification 0.44 N/mm	ASTM D903	<u>Results</u> 1.14	Status Pass
SECTION 3.2 Peel Strength, Foam to Plastic Membrane 3.2.1, Foam to Plastic Membrane, As Received	Specification No Delamination	ASTM D903	<u>Results</u> NA	Status NA
SECTION 3.3 Bond Separation	<u>Specification</u>	ASTM D1000	Results	<u>Status</u>

No Separation of Bond From an Actual

Production Part

CERTIFIED BY:

3.3, 200 gram load, 1 hr @ RT

Jake Cowdrick, Automotive Application Specialist

1-1-24 ISSUE DATE:

6-16-2015

Page 1 of 1

NT

Not Tested

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.