



TEST REPORT

250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

PRODUCT: FT 8392 12 PT BD
SUPPORT: PET FOAM
SUBSTRATE: ABS
CERT NO.: 221209 - 0917



FORD ESA-M11P19-A
OEM Rev Date: Jun 07
Adhesion Requirements
Polyurethane Foam to Polypropylene - Pressure Sensitive Film

TAPE REQUIREMENTS:

3 Standard Requirements for Production Materials
SECTION 3.1 Peel Strength, Plastic Membrane to Panel
3.1.1, As Received

Specification ASTM D903 Results Status
0.44 N / mm 0.8 Pass

SECTION 3.1 Peel Strength, Plastic Membrane to Panel
3.1.2, Aged, Heat Aged, 7 days @ 88°C

Specification ASTM D903 Results Status
0.44 N / mm 1.4 Pass

SECTION 3.1 Peel Strength, Plastic Membrane to Panel
3.1.2, Humidity, 7 days @ 37°C / 95% RH

Specification ASTM D903 Results Status
0.44 N / mm 1.0 Pass

SECTION 3.2 Peel Strength, Foam to Plastic Membrane
3.2.1, Foam to Plastic Membrane, As Received

Specification ASTM D903 Results Status
No Delamination Foam Tearing Pass

SECTION 3.3 Bond Separation
3.3, 200 gram load, 1 hr @ RT

Specification Results Status
No Separation of Bond No Slip Pass

SECTION 3.4 Quality
3.4 Quality

Specification Results Status
Readily Removable Easily Removed Pass

CERTIFIED BY:

Signature of Jake Cowdrick
Jake Cowdrick, Automotive Application Specialist

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.