



250 Chester Street
 Painesville, Ohio 44077
 Phone: **866-GO-AVERY (866-462-8379)**
 Fax: **888-358-4469**
 email: **psa.tape@averydennison.com**
 URL: **tapes.averydennison.com**

TEST REPORT

PRODUCT: **FBR 1950 12 PT BD**
 SUPPORT: **NITRILE VINYL FOAM**
 SUBSTRATE: **PP**
 CERT NO.: **221209 - 1418**



FORD ESB-M11P8-A
 OEM Rev Date: Jun 07
 Adhesion Requirements, PSA Sponge Rubber

TAPE REQUIREMENTS:

3 Standard Requirements for Production Materials

SECTION	Adhesion	ASTM D903	Specification	Results	Status
3.1.1,	As Received		0.66 N / mm	.53 Tear	Pass

SECTION 3.1	Adhesion	ASTM D903	Specification	Results	Status
3.1.2.1,	Aged, Heat Aged, 14 days @ 88°C		0.22 N / mm	0.47	Pass

SECTION 3.1	Adhesion	ASTM D903	Specification	Results	Status
3.1.2.1,	Aged, Humidity Aged, 14 days @ 37°C / 95% RH		0.44 N / mm	0.57	Pass

CERTIFIED BY:


 Jake Cowdrick, Automotive Application Specialist

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.