



250 Chester Street  
 Painesville, Ohio 44077  
 Phone: **866-GO-AVERY (866-462-8379)**  
 Fax: **888-358-4469**  
 email: **psa.tape@averydennison.com**  
 URL: **tapes.averydennison.com**

**TEST REPORT**

PRODUCT: **FBR 1950**  
 SUPPORT: **EPDM FOAM**  
 SUBSTRATE: **PAINTED METAL**  
 CERT NO.: **221209 - 1417**



**FORD ESB-M11P8-A**  
 OEM Rev Date: Jun 07  
 Adhesion Requirements, PSA Sponge Rubber

**TAPE REQUIREMENTS:**

**3 Standard Requirements for Production Materials**

SECTION	Adhesion	ASTM D903	Specification	Results	Status
3.1.1,	As Received		<b>0.66 N / mm</b>	.68 Tear	<b>Pass</b>

SECTION 3.1	<b>Adhesion</b>	ASTM D903	<b>Specification</b>	<b>Results</b>	<b>Status</b>
3.1.2.1,	Aged, Heat Aged, 14 days @ 88°C		<b>0.22 N / mm</b>	0.38	<b>Pass</b>

SECTION 3.1	<b>Adhesion</b>	ASTM D903	<b>Specification</b>	<b>Results</b>	<b>Status</b>
3.1.2.1,	Aged, Humidity Aged, 14 days @ 37°C / 95% RH		<b>0.44 N / mm</b>	0.60	<b>Pass</b>

CERTIFIED BY:

  
 Jake Cowdrick, Automotive Application Specialist

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.