



TEST REPORT

250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

PRODUCT: FBR 1950
SUPPORT: NITRILE VINYL FOAM
SUBSTRATE: PP
CERT NO.: 221209 - 1418



FORD ESB-M11P8-A
OEM Rev Date: Jun 07
Adhesion Requirements, PSA Sponge Rubber

TAPE REQUIREMENTS:

3 Standard Requirements for Production Materials

SECTION 3.1 Adhesion ASTM D903 Specification Results Status
3.1.1, As Received 0.66 N / mm .55 Tear Pass

SECTION 3.1 Adhesion ASTM D903 Specification Results Status
3.1.2.1, Aged, Heat Aged, 14 days @ 88°C 0.22 N / mm 0.50 Pass

SECTION 3.1 Adhesion ASTM D903 Specification Results Status
3.1.2.1, Aged, Humidity Aged, 14 days @ 37°C / 95% RH 0.44 N / mm 0.59 Pass

CERTIFIED BY:

Signature of Jake Cowdrick
Jake Cowdrick, Automotive Application Specialist

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.
This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.
Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.