

## **TEST REPORT**

PRODUCT:FBR 8950SUPPORT:NITRILE VINYL FOAMSUBSTRATE:PPCERT NO.:221209 - 1312



250 Chester StreetPainesville, Ohio 44077Phone:866-GO-AVERY (866-462-8379)Fax:888-358-4469email:psa.tape@averydennison.comURL:tapes.averydennison.com

3.1.2.1, Aged, Heat Aged, 14 days @ 88°C

## FORD ESB-M11P8-A

OEM Rev Date: Jun 07 Adhesion Requirements, PSA Sponge Rubber

TAPE REQUIREM3StandSECTION 3.13.1.1, As Received	ard Requirements for Adhesion	Production Materials ASTM D903	Specification 0.66 N / mm	<u>Results</u> 0.78	<u>Status</u> Pass
SECTION 3.1	Adhesion	ASTM D903	Specification	<u>Results</u>	<u>Status</u>

 SECTION 3.1
 Adhesion
 ASTM D903

 3.1.2.1, Aged, Humidity Aged, 14 days @ 37°C / 95% RH

Specification 0.44 N / mm

0.22 N/mm

<u>Results</u> 0.37 \* Tear

0.73

Status Pass

Pass

CERTIFIED BY:

Jake Cowdrick, Automotive Application Specialist

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.

Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077

Original Test Date: 12-5-2011 Page 1 of 1