



250 Chester Street
 Painesville, Ohio 44077
 Phone: 866-GO-AVERY (866-462-8379)
 Fax: 888-358-4469
 email: psa.tape@averydennison.com
 URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT B EZ
 SUPPORT: EPDM FOAM
 SUBSTRATE: ABS
 CERT NO.: 221209 - 1304



FORD ESB-M11P8-A
 OEM Rev Date: Jun 07
 Adhesion Requirements, PSA Sponge Rubber

TAPE REQUIREMENTS:

3 Standard Requirements for Production Materials
SECTION 3.1 Adhesion
 3.1.1, As Received

ASTM D903-98 10

Specification
0.66 N / mm

Results
 0.94

Status
Pass

SECTION 3.1 Adhesion
 3.1.2.1, Aged, Heat Aged, 14 days @ 88°C

Specification
0.22 N / mm

Results
 1.00

Status
Pass


SECTION 3.1 Adhesion
 3.1.2.1, Aged, Humidity Aged, 14 days @ 37°C / 95% RH

Specification
0.44 N / mm

Results
 0.67

Status
Pass

CERTIFIED BY:



Jake Cowdrick, Automotive Application Specialist

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.
 This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.
 Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.