



TEST REPORT

250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

PRODUCT: FT B EZ
SUPPORT: PORON FOAM
SUBSTRATE: ABS
CERT NO.: 221209 - 1305



FORD ESB-M11P8-A
OEM Rev Date: Jun 07
Adhesion Requirements, PSA Sponge Rubber

TAPE REQUIREMENTS:

3 Standard Requirements for Production Materials

SECTION 3.1 Adhesion

3.1.1, As Received

ASTM D903

Specification

0.66 N / mm

Results

0.75

Status

Pass

SECTION 3.1 Adhesion

3.1.2.1, Aged, Heat Aged, 14 days @ 88°C

Specification

0.22 N / mm

Results

0.76

Status

Pass

SECTION 3.1 Adhesion

3.1.2.1, Aged, Humidity Aged, 14 days @ 37°C / 95% RH

Specification

0.44 N / mm

Results

0.51

Status

Pass

CERTIFIED BY:

Signature of Jake Cowdrick, Automotive Application Specialist

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.