



TEST REPORT

250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

PRODUCT: FT B
SUPPORT: PORON FOAM
SUBSTRATE: PAINTED METAL
CERT NO.: 221209 - 1304

FORD ESB-M11P8-A
OEM Rev Date: Jun 07
Adhesion Requirements, PSA Sponge Rubber



TAPE REQUIREMENTS:

3 Standard Requirements for Production Materials
SECTION 3.1 Adhesion
3.1.1, As Received

Table with 3 columns: Specification (ASTM D903, 0.66 N/mm), Results (0.78), Status (Pass)

SECTION 3.1 Adhesion
3.1.2.1, Aged, Heat Aged, 14 days @ 88°C

Table with 3 columns: Specification (0.22 N/mm), Results (0.82), Status (Pass)

SECTION 3.1 Adhesion
3.1.2.1, Aged, Humidity Aged, 14 days @ 37°C / 95% RH

Table with 3 columns: Specification (0.44 N/mm), Results (1.35), Status (Pass)

CERTIFIED BY:

Signature of Jake Cowdrick, Automotive Application Specialist

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.
This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.
Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.
This laboratory is not accredited for the calibrations or tests marked *.