

250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

Fax: 888-358-4469

email: psa.tape@averydennison.com
URL: tapes.averydennison.com

16 hrs @ -29° C

TEST REPORT

PRODUCT: FT 8302
SUPPORT: EPDM FOAM
SUBSTRATE: PAINTED METAL
CERT NO.: 221209 - 0842

FORD ESB-M3G76-B2

OEM Rev Date: Sep 05 Tape, PET - Two Sided PSA ANSI National Accreditation Board
A C C R E D | T E D

ISO/IEC 17025
TESTING LABORATORY

TAPF	RFO	UIRFN	MENTS:

SECTION 3.6.1 Peel Adhesion 3.6.1, Peel Adhesion, As Received, Initial RT	ASTM D3330	Specification 219 N/m	<u>Results</u> 840.0	<u>Status</u> Pass
SECTION 3.6.2 Aged 3.6.2, Aged, Aged, 72 hrs @ RT	ASTM D3330	Specification 657 N/m	Results 1507.3	Status Pass
SECTION 3.6.3 Aged, Cycles 3.6.3, Aged, Cycles, CycleTest (5x) 4 hrs @ 70° C 4 hrs @ 38° C / 95% RH 16 hrs @ -29° C 4 hrs @ 38° C / 95% RH 4 hrs @ 70° C	ASTM D3330	Specification 438 N / m	<u>Results</u> 1039.7	Status Pass

SECTION 3.7	Migration Stain	FLTM BO 115-1*	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.7, Migration Stai	n, 48 Hour Fluorescence, White En	amel	None	Not Applicable	NA

SECTION 3.8	Liner Removal	ASTM D3330	Specification	Results	<u>Status</u>
3.8, Liner Remov	al, Initial Release		55 N/m	16.3	Pass

SECTION 3.9	Storage Stability	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.9, Storage Stab	ility, Liner Removal after 12 Months Below 32°C	No Appreciable Difference	Not Tested	TBD

CERTIFIED BY:

Jake Cowdrick, Automotive Application Specialist

ISSUE DATE: <u>1-1-24</u>

5-11-2005

Page 1 of 1

Original Test Date:

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.