

888-358-4469

866-GO-AVERY (866-462-8379)

psa.tape@averydennison.com

Peel Adhesion

tapes.averydennison.com

250 Chester Street

Phone:

Fax:

email:

URL:

Painesville, Ohio 44077

TAPE REQUIREMENTS:

SECTION 3.6.1

TEST REPORT

Specification

PRODUCT: FT 8302 SUPPORT: NITRILE VINYL FOAM SUBSTRATE: ABS 221209 - 0842 CERT NO .:



Status

Results

FORD ESB-M3G76-B2

ASTM D3330

OEM Rev Date: Sep 05 Tape, PET - Two Sided PSA

1049.0 3.6.1, Peel Adhesion, As Received, Initial RT 219 N/m Pass SECTION 3.6.2 Specification Aged ASTM D3330 **Results** Status 3.6.2, Aged, Aged, 72 hrs @ RT 657 N/m 1300.6 Pass SECTION 3.6.3 Aged, Cycles ASTM D3330 Specification **Results** Status 438 N/m 1050.2 3.6.3, Aged, Cycles, CycleTest (5x) Pass 4 hrs @ 70° C 4 hrs @ 38° C / 95% RH 16 hrs @ -29° C 4 hrs @ 38° C / 95% RH 4 hrs @ 70° C 16 hrs @ -29° C SECTION 3.7 **Migration Stain** FLTM BO 115-1* Specification **Results** Status Not Applicable None 3.7, Migration Stain, 48 Hour Fluorescence, White Enamel NA SECTION 3.8 **Liner Removal** ASTM D3330 Specification Results Status 3.8. Liner Removal. Initial Release 55 N/m 16.3 Pass

SECTION 3.9 **Storage Stability** 3.9, Storage Stability, Liner Removal after 12 Months Below 32°C

Specification No Appreciable Difference

Results Status Not Tested TBD

CERTIFIED BY:

e Cowdrick, Automotive Application Specialist

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience. This laboratory is not accredited for the calibrations or tests marked *.

Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077

Original Test Date: