



250 Chester Street  
 Painesville, Ohio 44077  
 Phone: 866-GO-AVERY (866-462-8379)  
 Fax: 888-358-4469  
 email: psa.tape@averydennison.com  
 URL: tapes.averydennison.com

**TEST REPORT**

PRODUCT: FT 8302  
 SUPPORT: NITRILE VINYL FOAM  
 SUBSTRATE: PP  
 CERT NO.: 221209 - 0842



**FORD ESB-M3G76-B2**  
 OEM Rev Date: Sep 05  
 Tape, PET - Two Sided PSA

**TAPE REQUIREMENTS:**

SECTION	TEST DESCRIPTION	STANDARD	Specification	Results	Status
SECTION 3.6.1	<b>Peel Adhesion</b>	ASTM D3330			
3.6.1,	Peel Adhesion, As Received, Initial RT		219 N / m	1057.2	Pass
SECTION 3.6.2	<b>Aged</b>	ASTM D3330			
3.6.2,	Aged, Aged, 72 hrs @ RT		657 N / m	1168.1	Pass
SECTION 3.6.3	<b>Aged, Cycles</b>	ASTM D3330			
3.6.3,	Aged, Cycles, CycleTest (5x)		438 N / m	1179.2	Pass
	4 hrs @ 70° C				
	4 hrs @ 38° C / 95% RH				
	16 hrs @ -29° C				
	4 hrs @ 38° C / 95% RH				
	4 hrs @ 70° C				
	16 hrs @ -29° C				
SECTION 3.7	<b>Migration Stain</b>	FLTM BO 115-1*			
3.7,	Migration Stain, 48 Hour Fluorescence, White Enamel		None	Not Applicable	NA
SECTION 3.8	<b>Liner Removal</b>	ASTM D3330			
3.8,	Liner Removal, Initial Release		55 N / m	16.3	Pass
SECTION 3.9	<b>Storage Stability</b>				
3.9,	Storage Stability, Liner Removal after 12 Months Below 32°C		No Appreciable Difference	Not Tested	TBD

CERTIFIED BY:

  
 Jake Cowdrick, Automotive Application Specialist

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.