

250 Chester Street Painesville, Ohio 44077

866-GO-AVERY (866-462-8379) Phone:

Fax: 888-358-4469

email: psa.tape@averydennison.com URL: tapes.averydennison.com

> 4 hrs @ 70° C 16 hrs @ -29° C

TEST REPORT

PRODUCT: FT 8392 12 PT BD

SUPPORT: 2 MIL PET

SUBSTRATE: SS

230109 - 1042 CERT NO .:

FORD ESB-M3G76-B2

OEM Rev Date: Sep 05 Tape, PET - Two Sided PSA



TAPE REQUIRE	EMENTS:
--------------	---------

SECTION 3.6.1 Peel Adhesion	ASTM D1000	Specification	<u>Results</u>	<u>Status</u>
3.6.1, Peel Adhesion, As Received, Initial RT		219 N/m	1229.4	Pass
SECTION 3.6.2 Aged	ASTM D1000	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.6.2, Aged, Aged, 72 hrs @ RT		657 N/m	1408.6	Pass
SECTION 3.6.3 Aged, Cycles	ASTM D1000	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.6.3, Aged, Cycles, CycleTest (5x)		438 N/m	1523.0	Pass
4 hrs @ 70° C				
4 hrs @ 38° C / 95% RH				
16 hrs @ -29° C				
4 hrs @ 38° C / 95% RH				

SECTION 3.7	Migration Stain	FLTM BO 115-01*	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.7, Migration Sta	ain, 48 Hour Fluorescence	, White Enamel	None	Not Applicable	NA

SECTION 3.8 Liner Removal	ASTM D1000	Specification	Results	<u>Status</u>
3.8, Liner Removal, Initial Release		55 N/m	17.5	Pass

SECTION 3.9	Storage Stability	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.9, Storage Stab	ility, Liner Removal after 12 Months Below 32°C	No Appreciable Difference	Not Tested	TBD

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-24

7-23-2001

Page 1 of 1

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.