

250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

Fax: 888-358-4469

email: psa.tape@averydennison.com
URL: tapes.averydennison.com

TEST REPORT

PRODUCT: FT 8392 SUPPORT: 2 MIL PET

SUBSTRATE: PP

CERT NO.: 230109 - 1042

FORD ESB-M3G76-B2

OEM Rev Date: Sep 05
Tape, PET - Two Sided PSA



TAPE	REQU	IREMEI	NTS:
------	------	--------	------

SECTION 3.6.1 Peel Adhesion	ASTM D1000	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.6.1, Peel Adhesion, As Received, Initial RT		219 N/m	1131.9	Pass

SECTION 3.6.2 Aged	ASTM D1000	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.6.2 Aged Aged 72 hrs @ RT		657 N/m	1250.4	Pass

3.6.2, Aged, Aged, 72 hrs @ R1	657 N/m

SECTION 3.6.3 Aged, Cycles	ASTM D1000	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.6.3, Aged, Cycles, CycleTest (5x)		438 N/m	1171.0	Pass

3.6.3, Aged, Cycles, CycleTest (5x) 4 hrs @ 70° C

CERTIFIED BY:

4 hrs @ 38° C / 95% RH

16 hrs @ -29° C

4 hrs @ 38° C / 95% RH

4 hrs @ 70° C 16 hrs @ -29° C

SECTION 3.7	Migration Stain	FLTM BO 115-01*	Specification	<u>Results</u>	<u>Status</u>
3.7, Migration Sta	ain, 48 Hour Fluorescence	e, White Enamel	None	Not Applicable	NA

• • • •	,g. a,	 	•			

SECTION 3.8	Liner Removal	ASTM D1000	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.8 Liner Remov	/al_Initial Release		55 N/m	25.1	Pass

SECTION 3.9 Storage Stability Specification Results Status 3.9, Storage Stability, Liner Removal after 12 Months Below 32°C No Appreciable Difference Not Tested TBD

Dave Nichols Jr, Automotive Lab Technician

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

ISSUE DATE:

1-1-24

Page 1 of 1