



250 Chester Street  
Painesville, Ohio 44077  
Phone: **866-GO-AVERY (866-462-8379)**  
Fax: **888-358-4469**  
email: **psa.tape@averydennison.com**  
URL: **tapes.averydennison.com**

### TEST REPORT

PRODUCT: **FBR 8950 12 PT BD**  
SUPPORT: **EPDM FOAM**  
SUBSTRATE: **ABS**  
CERT NO.: **221209 - 0852**



**FORD ESB-M3G76-B2**  
OEM Rev Date: Sep 05  
Tape, PET - Two Sided PSA

#### TAPE REQUIREMENTS:

SECTION	TEST DESCRIPTION	STANDARD	Specification	Results	Status
SECTION <b>3.6.1</b>	<b>Peel Adhesion</b>	ASTM D3330			
3.6.1,	Peel Adhesion, As Received, Initial RT		<b>219 N / m</b>	807.3	<b>Pass</b>
SECTION <b>3.6.2</b>	<b>Aged</b>	ASTM D3330			
3.6.2,	Aged, Aged, 72 hrs @ RT		<b>657 N / m</b>	1186.2	<b>Pass</b>
SECTION <b>3.6.3</b>	<b>Aged, Cycles</b>	ASTM D3330			
3.6.3,	Aged, Cycles, CycleTest (5x)		<b>438 N / m</b>	871.0	<b>Pass</b>
	4 hrs @ 70° C				
	4 hrs @ 38° C / 95% RH				
	16 hrs @ -29° C				
	4 hrs @ 38° C / 95% RH				
	4 hrs @ 70° C				
	16 hrs @ -29° C				
SECTION <b>3.7</b>	<b>Migration Stain</b>	FLTM BO 115-1*			
3.7,	Migration Stain, 48 Hour Fluorescence, White Enamel		<b>None</b>	Not Applicable	<b>NA</b>
SECTION <b>3.8</b>	<b>Liner Removal</b>	ASTM D3330			
3.8,	Liner Removal, Initial Release		<b>55 N / m</b>	10.5	<b>Pass</b>
SECTION <b>3.9</b>	<b>Storage Stability</b>				
3.9,	Storage Stability, Liner Removal after 12 Months Below 32°C		<b>No Appreciable Difference</b>	Not Tested	<b>TBD</b>

CERTIFIED BY:

  
Jake Cowdrick, Automotive Application Specialist

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.