



250 Chester Street
 Painesville, Ohio 44077
 Phone: **866-GO-AVERY (866-462-8379)**
 Fax: **888-358-4469**
 email: **psa.tape@averydennison.com**
 URL: **tapes.averydennison.com**

TEST REPORT

PRODUCT: **FT B 12 PT BD**
 SUPPORT: **EPDM FOAM**
 SUBSTRATE: **PAINTED METAL**
 CERT NO.: **221209 - 0841**


FORD ESB-M3G76-B2
 OEM Rev Date: Sep 05
 Tape, PET - Two Sided PSA



TAPE REQUIREMENTS:

| SECTION | TEST DESCRIPTION | ASTM | Specification | Results | Status |
|----------------------|--|----------------|----------------------------------|----------------|-------------|
| SECTION 3.6.1 | Peel Adhesion | ASTM D3330 | 219 N / m | 840.0 | Pass |
| 3.6.1, | Peel Adhesion, As Received, Initial RT | | | | |
| SECTION 3.6.2 | Aged | ASTM D3330 | 657 N / m | 1507.3 | Pass |
| 3.6.2, | Aged, Aged, 72 hrs @ RT | | | | |
| SECTION 3.6.3 | Aged, Cycles | ASTM D3330 | 438 N / m | 1039.7 | Pass |
| 3.6.3, | Aged, Cycles, CycleTest (5x) 4 hrs @ 70° C 4 hrs @ 38° C / 95% RH 16 hrs @ -29° C 4 hrs @ 38° C / 95% RH 4 hrs @ 70° C 16 hrs @ -29° C | | | | |
| SECTION 3.7 | Migration Stain | FLTM BO 115-1* | None | Not Applicable | NA |
| 3.7, | Migration Stain, 48 Hour Fluorescence, White Enamel | | | | |
| SECTION 3.8 | Liner Removal | ASTM D3330 | 55 N / m | 24.5 | Pass |
| 3.8, | Liner Removal, Initial Release | | | | |
| SECTION 3.9 | Storage Stability | | No Appreciable Difference | Not Tested | TBD |
| 3.9, | Storage Stability, Liner Removal after 12 Months Below 32°C | | | | |

CERTIFIED BY:



Jake Cowdrick, Automotive Application Specialist

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.