



250 Chester Street  
Painesville, Ohio 44077  
Phone: 866-GO-AVERY (866-462-8379)  
Fax: 888-358-4469  
email: psa.tape@averydennison.com  
URL: tapes.averydennison.com

### TEST REPORT

PRODUCT: FT B 12 PT BD  
SUPPORT: NITRILE VINYL FOAM  
SUBSTRATE: SS  
CERT NO.: 221209 - 0841


FORD ESB-M3G76-B2  
OEM Rev Date: Sep 05  
Tape, PET - Two Sided PSA



#### TAPE REQUIREMENTS:

SECTION	TEST DESCRIPTION	ASTM	Specification	Results	Status
3.6.1	Peel Adhesion, As Received, Initial RT	ASTM D3330	219 N / m	1162.8	Pass
3.6.2	Aged, Aged, 72 hrs @ RT	ASTM D3330	657 N / m	1258.6	Pass
3.6.3	Aged, Cycles, CycleTest (5x) 4 hrs @ 70° C 4 hrs @ 38° C / 95% RH 16 hrs @ -29° C 4 hrs @ 38° C / 95% RH 4 hrs @ 70° C 16 hrs @ -29° C	ASTM D3330	438 N / m	1385.3	Pass
3.7	Migration Stain, 48 Hour Fluorescence, White Enamel	FLTM BO 115-1*	None	Not Applicable	NA
3.8	Liner Removal, Initial Release	ASTM D3330	55 N / m	24.5	Pass
3.9	Storage Stability, Liner Removal after 12 Months Below 32°C		No Appreciable Difference	Not Tested	TBD

CERTIFIED BY:

  
Jake Cowdrick, Automotive Application Specialist

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.