

250 Chester Street Painesville, Ohio 44077

Phone: 866-GO-AVERY (866-462-8379)

Fax: 888-358-4469

email: psa.tape@averydennison.com URL:

tapes.averydennison.com

16 hrs @ -29° C

TEST REPORT

PRODUCT: FT B EZ

SUPPORT: NITRILE VINYL FOAM SUBSTRATE: PAINTED METAL 221209 - 0841 CERT NO .:

FORD ESB-M3G76-B2

OEM Rev Date: Sep 05 Tape, PET - Two Sided PSA



TAPE	REQU	IREM	IENTS:
-------------	------	------	--------

SECTION 3.6.1 Peel Adhesion 3.6.1, Peel Adhesion, As Received, Initial RT	ASTM D3330	Specification 219 N/m	<u>Results</u> 1130.2	<u>Status</u> Pass
SECTION 3.6.2 Aged 3.6.2, Aged, Aged, 72 hrs @ RT	ASTM D3330	Specification 657 N/m	Results 1190.3	Status Pass
SECTION 3.6.3 Aged, Cycles 3.6.3, Aged, Cycles, CycleTest (5x) 4 hrs @ 70° C 4 hrs @ 38° C / 95% RH 16 hrs @ -29° C 4 hrs @ 38° C / 95% RH 4 hrs @ 70° C	ASTM D3330	Specification 438 N / m	<u>Results</u> 1221.2	Status Pass

SECTION 3.7	Migration Stain	FLTM BO 115-1*	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.7, Migration Sta	ain, 48 Hour Fluorescence	, White Enamel	None	Not Applicable	NA

SECTION 3.8	Liner Removal	ASTM D3330	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.8, Liner Remova	al, Initial Release		55 N/m	15.8	Pass

SECTION 3.9	Storage Stability	<u>Specification</u>	<u>Results</u>	<u>Status</u>
3.9, Storage Stab	ility, Liner Removal after 12 Months Below 32°C	No Appreciable Difference	Not Tested	TBD

CERTIFIED BY:

Jake Cowdrick, Automotive Application Specialist

ISSUE DATE: 1-1-24

5-11-2005

Page 1 of 1

Original Test Date:

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.