



250 Chester Street  
 Painesville, Ohio 44077  
 Phone: **866-GO-AVERY (866-462-8379)**  
 Fax: **888-358-4469**  
 email: **psa.tape@averydennison.com**  
 URL: **tapes.averydennison.com**

**TEST REPORT**

PRODUCT: **FT B EZ**  
 SUPPORT: **NITRILE VINYL FOAM**  
 SUBSTRATE: **PP**  
 CERT NO.: **221209 - 0841**




**FORD ESB-M3G76-B2**  
 OEM Rev Date: Sep 05  
 Tape, PET - Two Sided PSA

**TAPE REQUIREMENTS:**

SECTION	TEST DESCRIPTION	STANDARD	Specification	Results	Status
SECTION 3.6.1	<b>Peel Adhesion</b> 3.6.1, Peel Adhesion, As Received, Initial RT	ASTM D3330	<b>219 N / m</b>		
SECTION 3.6.2	<b>Aged</b> 3.6.2, Aged, Aged, 72 hrs @ RT	ASTM D3330	<b>657 N / m</b>	1168.1	<b>Pass</b>
SECTION 3.6.3	<b>Aged, Cycles</b> 3.6.3, Aged, Cycles, CycleTest (5x) 4 hrs @ 70° C 4 hrs @ 38° C / 95% RH 16 hrs @ -29° C 4 hrs @ 38° C / 95% RH 4 hrs @ 70° C 16 hrs @ -29° C	ASTM D3330	<b>438 N / m</b>	1179.2	<b>Pass</b>
SECTION 3.7	<b>Migration Stain</b> 3.7, Migration Stain, 48 Hour Fluorescence, White Enamel	FLTM BO 115-1*	<b>None</b>	Not Applicable	<b>NA</b>
SECTION 3.8	<b>Liner Removal</b> 3.8, Liner Removal, Initial Release	ASTM D3330	<b>55 N / m</b>	15.8	<b>Pass</b>
SECTION 3.9	<b>Storage Stability</b> 3.9, Storage Stability, Liner Removal after 12 Months Below 32°C		<b>No Appreciable Difference</b>	Not Tested	<b>TBD</b>

CERTIFIED BY:

  
 Jake Cowdrick, Automotive Application Specialist

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.