TEST REPORT



250 Chester Street Painesville. Ohio 44077

866-GO-AVERY (866-462-8379) Phone:

Fax: 888-358-4469

psa.tape@averydennison.com email: URL: tapes.averydennison.com

PRODUCT: FT B SUPPORT: **FELT** SUBSTRATE: ABS

221209 - 0903 CERT NO .:

FORD ESB-M3G76-B2

OEM Rev Date: Sep 05

Tape, PET - Two Sided PSA

ACCBEDITED TESTING LABORATORY

Status

Pass

Status

Pass

Status

Pass

Status

NA

Status

Pass

Results

840.6

Results

920.6

Results

767.6

Results

Results

TAPE REQUIREMENTS:

SECTION: 3.6.1 Peel Adhesion **ASTM D3330** Specification

219 N/m 3.6.1, Peel Adhesion, As Received, Initial RT

SECTION: 3.6.2 Aged **ASTM D3330** Specification

3.6.2, Aged, Aged, 72 hrs @ RT

SECTION: 3.6.3 Aged, Cycles **ASTM D3330 Specification**

3.6.3, Aged, Cycles, CycleTest (5x)

4 hrs @ 70° C

4 hrs @ 38° C / 95% RH

16 hrs @ -29° C

4 hrs @ 38° C / 95% RH

4 hrs @ 70° C 16 hrs @ -29° C

SECTION: 3.7 **Migration Stain**

Liner Removal

Storage Stability

FLTM BO 115-1*

Specification

657 N/m

438 N/m

None Not Applicable

3.7, Migration Stain, 48 Hour Fluorescence, White Enamel

ASTM D3330

Specification

55 N/m 21.6

3.8, Liner Removal, Initial Release

3.9, Storage Stability, Liner Removal after 12 Months Below 32°C

Specification

No Appreciable Difference

Results Not Tested

Page 1 of 1

Status TBD

CERTIFIED BY:

SECTION: 3.8

SECTION: 3.9

Jake Cowdrick, Automotive Application Specialist

ISSUE DATE: 1-1-24

11-26-2014

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.