PRODUCT: SUPPORT:

SUBSTRATE: PAINTED METAL 221209 - 0903 CERT NO .:

866-GO-AVERY (866-462-8379) Phone: Fax: 888-358-4469

psa.tape@averydennison.com email: URL: tapes.averydennison.com

FORD ESB-M3G76-B2 OEM Rev Date: Sep 05 Tape, PET - Two Sided PSA



TAPE REQUIREMENTS:

250 Chester Street

Painesville. Ohio 44077

SECTION: 3.6.1 Peel Adhesion **ASTM D3330 Specification** Results **Status** 219 N/m 792.2 **Pass**

TEST REPORT

FT B

FELT

3.6.1, Peel Adhesion, As Received, Initial RT

SECTION: 3.6.2 Aged **ASTM D3330** Specification Results **Status** 657 N/m 872.7 3.6.2, Aged, Aged, 72 hrs @ RT **Pass**

SECTION: 3.6.3 Aged, Cycles **ASTM D3330 Specification** Results **Status** 882.1 438 N/m **Pass**

3.6.3, Aged, Cycles, CycleTest (5x)

4 hrs @ 70° C

4 hrs @ 38° C / 95% RH

16 hrs @ -29° C

4 hrs @ 38° C / 95% RH

4 hrs @ 70° C 16 hrs @ -29° C

SECTION: 3.7 FLTM BO 115-1* Specification Results **Migration Stain Status**

3.7, Migration Stain, 48 Hour Fluorescence, White Enamel None Not Applicable NA

SECTION: 3.8 **Liner Removal ASTM D3330 Specification** Results **Status** 55 N/m

3.8, Liner Removal, Initial Release 21.6 **Pass**

SECTION: 3.9 **Storage Stability Specification** Results **Status**

No Appreciable Difference Not Tested **TBD** 3.9, Storage Stability, Liner Removal after 12 Months Below 32°C

CERTIFIED BY:

Jake Cowdrick, Automotive Application Specialist

ISSUE DATE: 1-1-24

11-26-2014

Page 1 of 1

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.