

888-358-4469

866-GO-AVERY (866-462-8379)

psa.tape@averydennison.com

tapes.averydennison.com

250 Chester Street

Phone:

Fax:

email: URL:

Painesville, Ohio 44077

TEST REPORT

PRODUCT:	FT B
SUPPORT:	FELT
SUBSTRATE:	PP
CERT NO .:	221209 - 0903

FORD ESB-M3G76-B2

OEM Rev Date: Sep 05

Tape, PET - Two Sided PSA



TAPE REQUIREMENTS: SECTION 3.6.1 Peel Adhesion ASTM D3330 Specification **Results** Status 219 N/m 807.3 3.6.1, Peel Adhesion, As Received, Initial RT Pass SECTION 3.6.2 Aged ASTM D3330 Specification Results Status 657 N/m 979.5 3.6.2, Aged, Aged, 72 hrs @ RT Pass SECTION : 3.6.3 Aged, Cycles ASTM D3330 Specification Results Status 1019.8 3.6.3, Aged, Cycles, CycleTest (5x) 438 N/m Pass 4 hrs @ 70° C 4 hrs @ 38° C / 95% RH 16 hrs @ -29° C 4 hrs @ 38° C / 95% RH 4 hrs @ 70° C 16 hrs @ -29° C SECTION : 3.7 FLTM BO 115-1* Specification **Results Migration Stain** Status 3.7, Migration Stain, 48 Hour Fluorescence, White Enamel None Not Applicable NA SECTION : 3.8 **Liner Removal** ASTM D3330 **Specification Results** Status 3.8, Liner Removal, Initial Release 55 N/m 21.6 Pass

SECTION : 3.9 **Storage Stability** 3.9, Storage Stability, Liner Removal after 12 Months Below 32°C

Specification No Appreciable Difference

Results Status Not Tested TBD

CERTIFIED BY:

Jake Cowdrick, Automotive Application Specialist

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience. This laboratory is not accredited for the calibrations or tests marked *.

Avery Dennison Performance Tapes 250 Chester St. Painesville, Ohio 44077 Original Test Date 11-26-2014 Page 1 of 1