TEST REPORT



250 Chester Street Painesville. Ohio 44077

866-GO-AVERY (866-462-8379) Phone:

Fax: 888-358-4469

psa.tape@averydennison.com email: URL: tapes.averydennison.com

PRODUCT: FT B SUPPORT: **FELT** SUBSTRATE: SS

221209 - 0903 CERT NO .:

FORD ESB-M3G76-B2

OEM Rev Date: Sep 05

Tape, PET - Two Sided PSA



TAPE REQUIREMENTS:

SECTION: 3.6.1 Peel Adhesion **ASTM D3330** Specification

219 N/m 3.6.1, Peel Adhesion, As Received, Initial RT

Results 837.1

SECTION: 3.6.2 Aged **ASTM D3330** Specification

657 N/m

Results **Status**

Status

Pass

Pass

Status

Pass

SECTION: 3.6.3 Aged, Cycles

3.6.2, Aged, Aged, 72 hrs @ RT

ASTM D3330

Specification

Results 965.5

925.3

3.6.3, Aged, Cycles, CycleTest (5x) 438 N/m

4 hrs @ 70° C

4 hrs @ 38° C / 95% RH

16 hrs @ -29° C

4 hrs @ 38° C / 95% RH

4 hrs @ 70° C

16 hrs @ -29° C

SECTION: 3.7 **Migration Stain**

FLTM BO 115-1*

Specification

Results **Status**

3.7, Migration Stain, 48 Hour Fluorescence, White Enamel

None

Not Applicable

SECTION: 3.8 **Liner Removal** **ASTM D3330**

Specification 55 N/m

Results 21.6

Status Pass

NA

3.8, Liner Removal, Initial Release

Results

Page 1 of 1

Status

3.9, Storage Stability, Liner Removal after 12 Months Below 32°C

Storage Stability

Specification No Appreciable Difference

Not Tested

TBD

CERTIFIED BY:

SECTION: 3.9

Jake Cowdrick, Automotive Application Specialist

ISSUE DATE: 1-1-24

11-26-2014

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request. This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes. Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.