



250 Chester Street
Painesville, Ohio 44077
Phone: **866-GO-AVERY (866-462-8379)**
Fax: **888-358-4469**
email: **psa.tape@averydennison.com**
URL: **tapes.averydennison.com**

TEST REPORT

PRODUCT: **FT B**
SUPPORT: **NITRILE VINYL FOAM**
SUBSTRATE: **PP**
CERT NO.: **221209 - 0840**


FORD ESB-M3G76-B2
OEM Rev Date: Sep 05
Tape, PET - Two Sided PSA



TAPE REQUIREMENTS:

SECTION	TEST DESCRIPTION	ASTM	Specification	Results	Status
SECTION 3.6.1	Peel Adhesion	ASTM D3330	219 N / m	1057.2	Pass
3.6.1, Peel Adhesion, As Received, Initial RT					
SECTION 3.6.2	Aged	ASTM D3330	657 N / m	1168.1	Pass
3.6.2, Aged, Aged, 72 hrs @ RT					
SECTION 3.6.3	Aged, Cycles	ASTM D3330	438 N / m	1179.2	Pass
3.6.3, Aged, Cycles, CycleTest (5x)					
4 hrs @ 70° C					
4 hrs @ 38° C / 95% RH					
16 hrs @ -29° C					
4 hrs @ 38° C / 95% RH					
4 hrs @ 70° C					
16 hrs @ -29° C					
SECTION 3.7	Migration Stain	FLTM BO 115-1*	None	Not Applicable	NA
3.7, Migration Stain, 48 Hour Fluorescence, White Enamel					
SECTION 3.8	Liner Removal	ASTM D3330	55 N / m	20.4	Pass
3.8, Liner Removal, Initial Release					
SECTION 3.9	Storage Stability		No Appreciable Difference	Not Tested	TBD
3.9, Storage Stability, Liner Removal after 12 Months Below 32°C					

CERTIFIED BY:



Jake Cowdrick, Automotive Application Specialist

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked *.