



250 Chester Street  
 Painesville, Ohio 44077  
 Phone: 866-GO-AVERY (866-462-8379)  
 Fax: 888-358-4469  
 email: psa.tape@averydennison.com  
 URL: tapes.averydennison.com

**TEST REPORT**

PRODUCT: FT 8392  
 SUPPORT: EPDM FOAM  
 SUBSTRATE: PP  
 CERT NO.: 221213 - 0744



**FORD ESH-M11P19-B**  
 OEM Rev Date: Dec 13  
 Adhesion Requirements, Cellular Rubber / Polyurethane Foam  
 Pressure Sensitive Film with Biocide

**TAPE REQUIREMENTS:**

**3 Requirements**

**SECTION: 3.1 Peel Strength**

3.1.1, As Received

Specification  
**0.44 N / mm**

ASTM D3330

Results  
 0.57

Status  
**Pass**

**SECTION: 3.1 Peel Strength**

3.1.2, Aged, Heat Aged, 7 days @ 88°C

Specification  
**0.44 N / mm**

Results  
 0.59

Status  
**Pass**

**SPEC: 3.1 Peel Strength**

3.1.2, Humidity, 7 days @ 37°C / 95% RH

Specification  
**0.44 N / mm**

Results  
 0.63

Status  
**Pass**

**SECTION: 3.2 Peel Strength**

3.2.1, Foam to Plastic Membrane, As Received

Specification  
**No Delamination**

Results  
 Foam Tearing

Status  
**Pass**

**SECTION: 3.3 Bond Separation**

3.3, 200 gram load, 1 hr @ RT

Specification  
**No Separation of Bond**

Results  
 No Slip

Status  
**Pass**

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Performance Tapes.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.