



250 Chester Street  
 Painesville, Ohio 44077  
 Phone: **866-GO-AVERY (866-462-8379)**  
 Fax: **888-358-4469**  
 email: **psa.tape@averydennison.com**  
 URL: **tapes.averydennison.com**

**TEST REPORT**

PRODUCT: **FT 8392**  
 SUPPORT: **PEU FOAM**  
 SUBSTRATE: **PAINTED METAL**  
 CERT NO.: **221213 - 0744**



**FORD ESH-M11P19-B**  
 OEM Rev Date: Mar 93  
 Adhesion Requirements, Cellular Rubber / Polyurethane Foam  
 Pressure Sensitive Film with Biocide

**TAPE REQUIREMENTS:**

**3 Requirements**

**SECTION 3.1 Peel Strength**

3.1.1, As Received

ASTM D3330

Specification

**0.44 N / mm**

Results

0.78

Status

**Pass**

**SECTION 3.1 Peel Strength**

3.1.2, Aged, Heat Aged, 7 days @ 88°C

Specification

**0.44 N / mm**

Results

1.05

Status

**Pass**

**SECTION 3.1 Peel Strength**

3.1.2, Humidity, 7 days @ 37°C / 95% RH

Specification

**0.44 N / mm**

Results

1.12

Status

**Pass**

**SECTION 3.2 Peel Strength**

3.2, Foam to Plastic Membrane, As Received

Specification

**No Delamination**

Results

Foam Tearing

Status

**Pass**

**SECTION 3.3 Bond Separation**

3.3, 200 gram load, 1 hr @ RT

ASTM D1000-04

Specification

**No Separation of Bond**

Results

No Slip

Status

**Pass**

**SECTION 3.4 Quality**

3.4, Quality

Specification

**Readily Removable**

Results

Easily Removed

Status

**Pass**

**SECTION 3.5 Bacteria / Fungus Resistance**

3.5, Bacteria / Fungus Resistance

Specification

**Must Pass**

Results

All Passed

Status

**Pass**

CERTIFIED BY:

Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE:

1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.

This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison Specialty Tape Division.

Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.

This laboratory is not accredited for the calibrations or tests marked \*.