



TEST REPORT

250 Chester Street
Painesville, Ohio 44077
Phone: 866-GO-AVERY (866-462-8379)
Fax: 888-358-4469
email: psa.tape@averydennison.com
URL: tapes.averydennison.com

PRODUCT: FT 8393 12 PT BD
SUPPORT: 2 MIL PET
SUBSTRATE: PP
CERT NO.: 230109 - 1101



FORD ESH-M11P19-B
OEM Rev Date: Jan 13
Adhesion Requirements, Cellular Rubber / Polyurethane Foam
Pressure Sensitive Film with Biocide

Tested in accordance with JDC protocols and provided as product information only. Actual product and application substrates would need to be tested for OEM certification.

TAPE REQUIREMENTS:

3 Requirements

SECTION 3.1 Peel Strength
3.1.1, As Received
ASTM D903
Specification: 0.44 N / mm
Results: 0.68
Status: Pass

SECTION 3.1 Peel Strength
3.1.2, Aged, Heat Aged, 7 days @ 88°C
ASTM D903
Specification: 0.44 N / mm
Results: 0.84
Status: Pass

SPEC: 3.1 Peel Strength
3.1.2, Humidity, 7 days @ 37°C / 95% RH
ASTM D903
Specification: 0.44 N / mm
Results: 0.89
Status: Pass

SECTION 3.2 Peel Strength
3.2.1, Foam to Plastic Membrane, As Received
ASTM D903
Specification: No Delamination
Results: No Delamination
Status: Pass

SECTION 3.3 Bond Separation
3.3, 200 gram load, 1 hr @ RT
ASTM D903
Specification: No Separation of Bond
Results: No Slip
Status: Pass

CERTIFIED BY: [Signature]
Dave Nichols Jr, Automotive Lab Technician

ISSUE DATE: 1-1-24

Materials tested to OEM requirements @ 72°F +/- 2°F and 50% RH +/- 5%. Test uncertainty and minor exclusions are available online or upon request.
This certificate or report shall not be reproduced except in full, without the written approval of the Avery Dennison® Performance Tapes.
Status opinion based upon measurements obtained by personnel with appropriate training and professional experience.